

## LAPRENE® NEUTRO 83K000994/P1 - SEBS

Physical properties	Value	Unit	Test Standard
Density	912	kg/m <sup>3</sup>	ISO 1183

Mechanical properties	Value	Unit	Test Standard
Shore A hardness, 3s	44	-	ISO 868

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	1.1	MPa	ISO 37
Tensile stress at 300% strain	2.2	MPa	ISO 37
Tensile strain at break (TPE)	482	%	ISO 37
Tensile stress at break (TPE)	3.2	MPa	ISO 37
Shore A hardness, 3s	44	-	ISO 868
Tear strength	19	kN/m	ISO 34-1

### Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	205 - 215	°C	-
Zone2 temperature	215 - 225	°C	-
Zone3 temperature	225 - 235	°C	-
Nozzle temperature	225 - 235	°C	-
Mold temperature	30 - 50	°C	-

### Other text information

#### Pre-drying

2h@80C

#### Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.

### Contact Information

#### Americas

8040 Dixie Highway  
 Florence, KY 41042 USA  
 Product Information Service  
 t: +1-800-833-4882  
 t: +1-859-372-3244  
 Customer Service  
 t: +1-800-526-4960  
 t: +1-859-372-3214  
 e: info-engineeredmaterials-am@celanese.com

#### Asia

4560 Jinke Road  
 Zhang Jiang Hi Tech Park  
 Shanghai 201203 PRC  
 Customer Service  
 t: +86 21 3861 9266  
 f: +86 21 3861 9599  
 e: info-engineeredmaterials-asia@celanese.com

#### Europe

Am Unisys-Park 1  
 65843 Sulzbach, Germany  
 Product Information Service  
 t: +49-800-86427-531  
 t: +49-(0)-69-45009-1011  
 e: info-engineeredmaterials-eu@celanese.com

### General Disclaimer

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this

---

## LAPRENE® NEUTRO 83K000994/P1 - SEBS

---

publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products. The products mentioned herein are not intended for use in medical or dental implants.

### Trademark

---

© 2014 Celanese or its affiliates. All rights reserved. (Published 27.July.2016). Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.