## **CAMPUS® Datasheet**





## **Product Texts**

LNP LUBRICOMP CL002 compound is based on Polystyrene (PS) resin containing 10% PTFE. Added features of this grade include: Wear Resistant.

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	2000	MPa	ISO 527-1/-2
Stress at break	27	MPa	ISO 527-1/-2
Strain at break	13.3	%	ISO 527-1/-2
Thermal properties	Value	Unit	Test Standard
Temp. of deflection under load, 1.80 MPa	84	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	94	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	76	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	84	E-6/K	ISO 11359-1/-2
Other properties	Value	Unit	Test Standard
Density	1110	kg/m³	ISO 1183

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.