

ENSOFT SL-154-60A

ENSOFT-S



Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is high mineral filled, completely recyclable and possible alternative to replace PVC in various applications. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer
Key Features :	Good ozone and UV resistance Easy processing Rubberlike elasticity Easy colorability with proper MB (PE, PP, etc. based)
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts (seals, tubes, profiles, hoses, etc.) for construction and furniture
Revision Date :	01.06.2013

	Value	Unit	Standard
Physical			
Hardness	60	SHORE A	ISO 868 (3 second)
Density	1,18	gr / cm3	ISO 1183 1-A
Brittleness Point	-55	°C	*
Mechanical			
100% Modulus	1,6	Mpa	ISO 37, DIN 53504
300% Modulus	2,3	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	5	Mpa	ISO 37, DIN 53504
Elongation at Break	660	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	22	kN/m	ISO 34-1
Aging			
Compression Set (72h/23°C)	25	%	ASTM D 395-89-B
Thermal			
Max. Dynamic Service Temperature	90	°C	*
Max. Static Service Temperature	110	°C	*

ENPLAST Plastik Kimya San. Tic. A.Ş
Address : Akse Mh. Fevzi Çakmak Cad. No : 130
Cayırova - Kocaeli 41420 Turkey
Tel : +90 262 672 10 50
Fax : +90 262 672 10 51
Mail : info@enplast.com.tr

www.enplast.com.tr

ENPLAST Americas, Inc.
Address : 616 111th Street, Arlington
Texas 76011 - USA
Tel : +1 817 635 47 70



ENSOFT SL-154-60A

ENSOFT-S



Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

Important Notice;

The above results are obtained from the tests conducted in Enplast laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. ENPLAST accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

ENPLAST Plastik Kimya San. Tic. A.Ş

Address : Akse Mh. Fevzi Çakmak Cad. No : 130

Cayırova - Kocaeli 41420 Turkey

Tel : +90 262 672 10 50

Fax : +90 262 672 10 51

Mail : info@enplast.com.tr

www.enplast.com.tr

ENPLAST Americas, Inc.

Address : 616 111th Street, Arlington

Texas 76011 - USA

Tel : +1 817 635 47 70

