

Technical Data

Product Description

CYCOLOY™ Resin
CP8320 - Europe

CYCOLOY Medium Heat Plating Grade for Automotive

Generic
PC+ABS

This data represents typical values that have been calculated from all products classified as: Generic PC +ABS

This information is provided for comparative purposes only.

General

CYCOLOY™ Resin
CP8320 - Europe

Generic
PC+ABS

Manufacturer / Supplier

- SABIC

- Generic

Generic Symbol

- PC+ABS

- PC+ABS

Material Status

- Commercial: Active

- Commercial: Active

Availability

- Europe

- Africa & Middle East
- Asia Pacific
- Europe
- Latin America
- North America

Uses

- Automotive Exterior Parts
- Electrical/Electronic Applications
- Rail Applications
- Water Management

--

Also Available In

- Asia Pacific

- Asia Pacific
- Europe
- Latin America
- North America

Physical

CYCOLOY™ Resin
CP8320 - Europe

Generic
PC+ABS

Unit

Test Method

Density / Specific Gravity

--

1.10

1.10 to 1.21

g/cm³

ASTM D792
ISO 1183

--

--

1.10 to 1.19

g/cm³

ASTM D1505

Apparent (Bulk) Density

--

0.60 to 0.65

g/cm³

ISO 60

Melt Mass-Flow Rate (MFR)

260°C/5.0 kg

14

4.8 to 30

g/10 min

ASTM D1238

260°C/5.0 kg

--

12 to 29

g/10 min

ISO 1133

Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)

13

8.0 to 49

cm³/10min

ISO 1133

Spiral Flow

--

39.6 to 68.6

cm

Molding Shrinkage

Flow

--

0.45 to 0.74

%

ASTM D955

Across Flow

--

0.54 to 0.62

%

ASTM D955

--

--

0.48 to 0.65

%

ISO 294-4

Flow : 3.20 mm

0.50 to 0.70

--

%

Internal Method

Water Absorption

24 hr

--

0.096 to 0.22

%

ASTM D570

24 hr, 23°C

--

0.088 to 0.70

%

ISO 62

Saturation

--

0.10 to 0.61

%

ASTM D570

Saturation, 23°C

0.30

0.090 to 0.70

%

ISO 62

Equilibrium, 23°C, 50% RH

0.10

0.057 to 0.25

%

ISO 62



Mechanical	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Tensile Modulus				
--	--	1850 to 3050	MPa	ASTM D638
-- ²	2100	--	MPa	ASTM D638
--	--	1620 to 3190	MPa	ISO 527-1
--	2100	--	MPa	ISO 527-1/1
Tensile Strength				
Yield ³	45.0	--	MPa	ASTM D638
Yield	--	48.4 to 65.2	MPa	ASTM D638
Yield	--	35.0 to 67.1	MPa	ISO 527-2
Yield	45.0	--	MPa	ISO 527-2/50
Break	--	39.2 to 62.3	MPa	ASTM D638
Break ³	40.0	--	MPa	ASTM D638
Break	--	39.2 to 58.5	MPa	ISO 527-2
Break	40.0	--	MPa	ISO 527-2/50
--	--	39.5 to 66.2	MPa	ASTM D638
--	--	47.8 to 60.5	MPa	ISO 527-2
Tensile Elongation				
Yield	--	1.5 to 21	%	ASTM D638
Yield ³	4.0	--	%	ASTM D638
Yield	--	2.5 to 7.4	%	ISO 527-2
Yield	4.0	--	%	ISO 527-2/50
Break	--	29 to 110	%	ASTM D638
Break ³	100	--	%	ASTM D638
Break	--	28 to 100	%	ISO 527-2
Break	100	--	%	ISO 527-2/50
Nominal Tensile Strain at Break	--	49 to 100	%	ISO 527-2
Flexural Modulus				
50.0 mm Span ⁴	2000	--	MPa	ASTM D790
--	--	2010 to 2770	MPa	ASTM D790
--	--	1810 to 2700	MPa	ISO 178
-- ⁵	2000	--	MPa	ISO 178
Flexural Strength				
--	--	68.4 to 105	MPa	ASTM D790
--	--	69.0 to 102	MPa	ISO 178
-- ^{5,6}	65.0	--	MPa	ISO 178
Yield	--	68.4 to 105	MPa	ASTM D790
Yield, 50.0 mm Span ⁴	70.0	--	MPa	ASTM D790
Break	--	63.7 to 83.7	MPa	ASTM D790
Taber Abrasion Resistance	--	54.0 to 82.0	mg	ASTM D1044
Impact	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Charpy Notched Impact Strength				
--	--	6.5 to 63	kJ/m ²	ISO 179
-30°C ⁷	30	--	kJ/m ²	ISO 179/1eA
23°C ⁷	60	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				
--	--	22 to 100	kJ/m ²	ISO 179
-30°C ⁷	No Break	--		ISO 179/1eU
23°C ⁷	No Break	--		ISO 179/1eU



Impact	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Notched Izod Impact				
--	--	48 to 710	J/m	ASTM D256
-30°C	400	--	J/m	ASTM D256
23°C	600	--	J/m	ASTM D256
--	--	9.0 to 57	kJ/m ²	ISO 180
-30°C ⁸	30	--	kJ/m ²	ISO 180/1A
23°C ⁸	60	--	kJ/m ²	ISO 180/1A
Notched Izod Impact (Area)	--	39.2 to 65.1	kJ/m ²	ASTM D256
Unnotched Izod Impact				
--	--	380 to 2200	J/m	ASTM D4812
--	--	94 to 100	kJ/m ²	ISO 180
-30°C ⁸	No Break	--		ISO 180/1U
23°C ⁸	No Break	--		ISO 180/1U
Instrumented Dart Impact				
--	--	42.8 to 65.3	J	ASTM D3763
23°C, Total Energy	55.0	--	J	ASTM D3763
--	--	35.0 to 105	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force	--	4260 to 5400	N	ISO 6603-2
Gardner Impact	--	35.6 to 36.3	J	ASTM D3029
Hardness	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Rockwell Hardness				
--	--	100 to 120		ASTM D785
--	--	106 to 124		ISO 2039-2
Shore Hardness	--	79 to 80		ISO 868
Ball Indentation Hardness	--	89.3 to 133	MPa	ISO 2039-1
Thermal	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	--	86.9 to 131	°C	ASTM D648
0.45 MPa, Unannealed	--	87.6 to 131	°C	ISO 75-2/B
0.45 MPa, Annealed	--	92.0 to 129	°C	ISO 75-2/B
1.8 MPa, Unannealed	--	79.9 to 116	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	90.0	--	°C	ASTM D648
1.8 MPa, Unannealed	--	78.9 to 113	°C	ISO 75-2/A
1.8 MPa, Unannealed, 4.00 mm, 64.0 mm Span ⁸	92.0	--	°C	ISO 75-2/Af
1.8 MPa, Annealed	--	94.6 to 110	°C	ISO 75-2/A
Continuous Use Temperature	--	60.0 to 100	°C	ASTM D794
Vicat Softening Temperature				
--	--	89.9 to 139	°C	ASTM D1525
--	106	--	°C	ASTM D1525 ⁹ ISO 306/B50 ⁹
--	107	--	°C	ISO 306/B120
--	--	92.5 to 141	°C	ISO 306
Ball Pressure Test (73 to 77°C)	Pass	--		IEC 60695-10-2



Thermal	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
CLTE				
Flow	--	7.1E-5 to 8.3E-5	cm/cm/°C	ASTM D696
Flow	--	5.3E-5 to 7.6E-5	cm/cm/°C	ASTM E831
Flow : -40 to 40°C	9.0E-5	--	cm/cm/°C	ASTM E831 ISO 11359-2
Flow	--	5.5E-5 to 1.0E-4	cm/cm/°C	ISO 11359-2
Transverse	--	6.9E-5 to 9.1E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	9.0E-5	--	cm/cm/°C	ASTM E831 ISO 11359-2
Transverse	--	5.6E-5 to 8.6E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity				
--	--	0.20 to 0.37	W/m/K	ASTM C177
--	0.20	0.20	W/m/K	ISO 8302
RTI Elec	--	60.0 to 90.4	°C	UL 746B
RTI Imp	--	60.0 to 90.0	°C	UL 746B
RTI Str	--	60.0 to 90.4	°C	UL 746B
Electrical	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Surface Resistivity				
--	--	1.0E+4 to 2.5E+15	ohms	ASTM D257
--	> 1.0E+15	5.1E+3 to 1.3E+16	ohms	IEC 60093
Volume Resistivity				
--	--	1.0 to 1.0E+17	ohms-cm	ASTM D257
--	> 1.0E+15	1.0E+11 to 5.0E+16	ohms-cm	IEC 60093
Dielectric Strength				
--	--	8.5 to 40	kV/mm	ASTM D149
--	--	15 to 37	kV/mm	IEC 60243-1
0.800 mm, in Oil	35	--	kV/mm	IEC 60243-1
1.60 mm, in Oil	25	--	kV/mm	IEC 60243-1
3.20 mm, in Oil	17	--	kV/mm	IEC 60243-1
Dielectric Constant				
--	--	3.00 to 3.01		ASTM D150
--	--	2.89 to 3.10		IEC 60250
--	--	2.95		IEC 60250
Dissipation Factor				
--	--	4.9E-3 to 9.1E-3		ASTM D150
--	--	1.0E-3 to 9.6E-3		IEC 60250
Arc Resistance	--	119 to 123	sec	ASTM D495
Comparative Tracking Index	--	218 to 600	V	IEC 60112
Flammability	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Burning Rate	--	33 to 100	mm/min	ISO 3795
Glow Wire Flammability Index	--	642 to 960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature	--	694 to 960	°C	IEC 60695-2-13
Oxygen Index				
--	--	28 to 32	%	ASTM D2863
--	--	23 to 34	%	ISO 4589-2
Fill Analysis	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit	Test Method
Melt Viscosity	--	170 to 255	Pa·s	ASTM D3835



Injection	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit
Drying Temperature	95 to 105	79 to 110	°C
Drying Time	2.0 to 4.0	2.7 to 5.0	hr
Drying Time, Maximum	--	6.0	hr
Suggested Max Moisture	0.020	0.020 to 0.024	%
Suggested Shot Size	--	50 to 55	%
Hopper Temperature	60 to 80	70 to 74	°C
Rear Temperature	220 to 250	218 to 266	°C
Middle Temperature	240 to 280	229 to 274	°C
Front Temperature	240 to 280	234 to 270	°C
Nozzle Temperature	230 to 270	249 to 273	°C
Processing (Melt) Temp	250 to 280	243 to 275	°C
Mold Temperature	60 to 90	59 to 86	°C
Injection Pressure	--	85.3 to 99.0	MPa
Holding Pressure	--	74.7 to 75.0	MPa
Back Pressure	--	0.138 to 10.0	MPa
Screw Speed	--	52 to 56	rpm
Vent Depth	--	0.050 to 0.057	mm

Injection Notes

Generic PC+ABS This data represents typical values that have been calculated from all products classified as: Generic PC+ABS
This information is provided for comparative purposes only.

Extrusion	CYCOLOY™ Resin CP8320 - Europe	Generic PC+ABS	Unit
Drying Temperature	--	89 to 95	°C
Drying Time	--	3.0 to 7.0	hr
Melt Temperature	--	250 to 257	°C

Extrusion Notes

Generic PC+ABS This data represents typical values that have been calculated from all products classified as: Generic PC+ABS
This information is provided for comparative purposes only.

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 5.0 mm/min
- ³ Type I, 50 mm/min
- ⁴ 1.3 mm/min
- ⁵ 2.0 mm/min
- ⁶ at Yield
- ⁷ 80*10*4 sp=62mm
- ⁸ 80*10*4 mm
- ⁹ Rate A (50°C/h), Loading 2 (50 N)

