

## Hostacom G3 U01 L

### Compounded Polyolefin

#### Product Description

"Hostacom G3 U01 L is a glass fiber reinforced PP homopolymer, with medium melt flow rate. Product is UL listed."

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

|                                      |                                 |     |
|--------------------------------------|---------------------------------|-----|
| <b>Status</b>                        | Commercial                      |     |
| <b>Availability</b>                  | Europe                          | (1) |
| <b>Processing Method</b>             | Injection molding               |     |
| <b>Features</b>                      | Medium melt flow rate.          |     |
| <b>Typical Customer Applications</b> | Used for standard applications. |     |

| Typical Properties                        | Method        | Value | Unit                    |
|---|---------------|-------|-------------------------|
| <b>Physical</b>                           |               |       |                         |
| Melt Flow Rate (230 °C, 2.16 kg)          | ISO 1133      | 15    | g/10 min                |
| Melt Volume Rate (230 °C, 2.16 kg)        | ISO 1133      | 15    | cm <sup>3</sup> /10 min |
| Density (23 °C)                           | ISO 1183-1/A  | 1.14  | g/cm <sup>3</sup>       |
| <b>Mechanical</b>                         |               |       |                         |
| Tensile Modulus (23 °C)                   | ISO 527-1, -2 | 6800  | MPa                     |
| Tensile Stress at Yield (23 °C)           | ISO 527-1, -2 | 95    | MPa                     |
| Tensile Strain at Yield (23 °C)           | ISO 527-1, -2 | 3.0   | %                       |
| Flexural Modulus (23 °C) Tech. A          | ISO 178/A1    | 5600  | MPa                     |
| <b>Impact</b>                             |               |       |                         |
| Charpy Impact Strength, unnotched (23 °C) | ISO 179-1/1eU | 40    | kJ/m <sup>2</sup>       |
| Charpy Impact Strength, notched (23 °C)   | ISO 179-1/1eA | 8     | kJ/m <sup>2</sup>       |
| <b>Thermal</b>                            |               |       |                         |
| Vicat Softening Temperature B (50 N)      | ISO 306       | 135   | °C                      |
| Heat Deflection Temperature A (1.8 MPa)   | ISO 75-1, -2  | 145   | °C                      |
| Heat Deflection Temperature B (0.45 MPa)  | ISO 75-1, -2  | 155   | °C                      |
| <b>Other</b>                              |               |       |                         |
| Flame Class (1.5 mm)                      | UL 94         | HB    | -                       |
| Flame Class (3.0 mm)                      | UL 94         | HB    | -                       |

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

#### Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.

© LyondellBasell Industries Holdings, B.V. 2014

LyondellBasell markets this product through the following entities:

- Equistar Chemicals, LP
- Basell Sales & Marketing Company B.V.
- Basell Asia Pacific Limited
- Basell International Trading FZE
- LyondellBasell Australia Pty Ltd

For the contact details of the LyondellBasell company selling this product in your country, please visit <http://www.lyondellbasell.com/>.

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally.

**SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT.**

This product(s) may not be used in:

- (i) any U.S. FDA Class I, Health Canada Class I, and/or European Union Class I Medical Devices, without prior notification to Seller for each specific product and application; or
- (ii) the manufacture of any of the following, without prior written approval by Seller for each specific product and application: (1) U.S. FDA Class II, Health Canada Class II or Class III, and/or European Union Class II Medical Devices; (2) film, overwrap and/or product packaging that is considered a part or component of one of the aforementioned Medical Devices; (3) packaging in direct contact with a pharmaceutical active ingredient and/or dosage form that is intended for inhalation, injection, intravenous, nasal, ophthalmic (eye), digestive, or topical (skin) administration; (4) tobacco related products and applications; (5) electronic cigarettes and similar devices; and (6) pressure pipe or fittings that are considered a part or component of a nuclear reactor.
- (iii) Additionally, the product(s) may not be used in: (1) U.S. FDA Class III, Health Canada Class IV, and/or European Class III Medical Devices; (2) applications involving permanent implantation into the body; (3) life-sustaining medical applications; and (4) lead, asbestos or MTBE related applications.

All references to U.S. FDA, Health Canada, and European Union regulations include another country's equivalent regulatory classification.

Users should review the applicable Material Safety Data Sheet before handling the product.

Addhere, Adflex, Adstif, Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Alkylate, Amazing Chemistry, Aquamarine, Aquathene, Arctic Plus, Arctic Shield, Avant, Catalloy, Clyrell, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Fueling the power to win, Get in touch with, Glacido, Hifax, Histif, Hostacom, Hostalen PP, Hostalen ACP, Ideal, Indure, Integrate, Koattro, LIPP, Lucalen, Luflexen, Lupolen, Lupolex, Luposim, Lupostress, Lupotech, Metocene, Microthene, Moplen, MPDIOL, Nerolex, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Prodflex, Pro-fax, Punctilious, Purell, Refax, SAA100, SAA101, Sequel, Softell, Spherilene, Spheripol, Spherizone, Starflex, Stretchene, Superflex, TBAC, Tebol, T-Hydro, Topyl, Trans4m, Tufflo, Ultrathene, Vacido and Valtec, are trademarks owned and/or used by the LyondellBasell family of companies.

Adsyl, Akoafloor, Akoalit, Alastian, Alathon, Aquamarine, Arctic Plus, Arctic Shield, Avant, CRP, Crystex, Dexflex, Duopac, Duoprime, Explore & Experiment, Filmex, Flexathene, Hifax, Hostacom, Hostalen, Ideal, Integrate, Koattro, Lucalen, Lupolen, Metocene, Microthene, Moplen, MPDIOL, Nexprene, Petrothene, Plexar, Polymeg, Pristene, Pro-fax, Punctilious, Purell, Sequel, Softell, Spheripol, Spherizone, Starflex, Tebol, T-Hydro, Topyl, Tufflo, Ultrathene are registered in the U.S. Patent and Trademark Office.

Release date: 11/03/2015