

Luran HH-120

Alpha-Methylstyrene Acrylonitrile (AMSAN)

TECHNICAL DATASHEET

DESCRIPTION

Luran® HH-120 is a grade of AMSAN with high heat resistance and improved mechanical strength. It is suitable for injection molding and extrusion applications and can be used as a modifier for high heat ABS and PVC. For TDS and further information about the specialty piano black versions of Luran® HH-120 including Styrolution's latest SPF50 UV protection technology please contact the Styrolution Infopoint.

FEATURES

- Outstanding heat resistance
- Very good mechanical strength
- Good surface appearance
- Excellent dimensional stability
- New SPF 50 UV stabilization available

APPLICATIONS

- Automotive parts
- Polymer blend additive

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	7
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	2
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	2
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	2
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m ²	20
Charpy Unnotched, -30 °C	ISO 179/1eU	kJ/m ²	21
Tensile Stress at Yield, 23 °C	ISO 527	MPa	79
Tensile Strain at Break, 23 °C	ISO 527	%	3
Tensile Modulus	ISO 527	MPa	3900
Flexural Strength, 23 °C	ISO 178	MPa	135
Hardness, Ball Indentation	ISO 2039-1	MPa	175
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	120
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	104

Luran HH-120

Alpha-Methylstyrene Acrylonitrile (AMSAN)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	110
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	70
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 60250	-	3
Dissipation Factor (100 Hz)	IEC 60250	10 ⁻⁴	50
Dissipation Factor (1 MHz)	IEC 60250	10 ⁻⁴	70
Volume Resistivity	IEC 60093	Ohm*m	10 ¹⁴
Surface Resistivity	IEC 60093	Ohm	>10 ¹⁵
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.567
Other Properties			
Density	ISO 1183	kg/m ³	1080
Bulk Density (with external lubricant)	-	kg/m ³	600
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.3
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 0.7
Melt Temperature Range	ISO 294	°C	220 - 270
Mold Temperature Range	ISO 294	°C	40 - 80
Injection Velocity	ISO 294	mm/s	200
Drying Temperature	-	°C	80
Drying Time	-	h	2 - 4

Typical values for uncolored products

SUPPLY FORM

Luran® HH is supplied as cylindrical or lenticular pellets. The bulk density is approx. 0.55-0.65 g/cm³. Standard pack: 25 kg PE sack, palletized and film-secured. PE bags should not be stored outside. Subject to agreement, other means of packing are possible, e.g. 1000 kg bulk containers (flexible IBCs or intermediate bulk big bag containers); shipping by road tanker can be arranged. Luran® pellets can be stored for prolonged periods in dry areas subject to normal temperature control without any changes in mechanical properties. However, for sensitive colors storage over some years can cause some color change. Under poor storage conditions, Luran absorbs moisture, which can be removed again by drying. Packs stored in cold areas should be brought to ambient temperature before opening, to prevent condensation on the pellets.

PROCESSING

Luran HH 120 can either be processed through injection molding or extrusion but any process suitable for thermoplastic resin compositions may also be used.

PRODUCT SAFETY

Given appropriate processing of the products and suitable ventilation measures in production areas, no adverse effects on the health of process operators have been found. Workplace limits for styrene and acrylonitrile, as given in the national listings applicable, must be adhered to. The values currently applicable in Germany under TRGS 900 (issue of October, 2002) for maximum workplace concentrations are as follows. Styrene: 20 ml/m³ = 86 mg/m³; acrylonitrile: 3 ml/m³ = 7 mg/m³. Appendix I of Directive 67/548/EWG and TRGS 905 (issue of October, 2002) classify acrylonitrile in carcinogenic category II (substances which should be regarded as carcinogenic in humans). Experience has shown that during appropriate processing of Luran with suitable ventilation the values obtained are well below the limits mentioned above. TRGS 402 (Germany) can be used for determining and assessing the concentrations of hazardous substances in the air within working areas. Inhalation of gaseous degradation products, such as those which may arise on severe overheating of the material or during pumped evacuation, must be avoided. Further information can be found in our Luran safety data sheets.

DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.