

| Thermal properties | dry / cond | Unit | Test Standard |
|---|-------------------|-------------|----------------------|
| ISO Data | | | |
| ^[C] Temp. of deflection under load, 1.80 MPa | 220 / * | °C | ISO 75-1/-2 |
| ^[C] Temp. of deflection under load, 0.45 MPa | 240 / * | °C | ISO 75-1/-2 |
| ^[C] Burning Behav. at 1.5 mm nom. thickn. | V-0 / * | class | IEC 60695-11-10 |
| Thickness tested | 1.5 / * | mm | - |

[C]: CAMPUS

| Other properties | dry / cond | Unit | Test Standard |
|-------------------------|-------------------|-------------------|----------------------|
| ^[C] Density | 1590 / - | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa