

SOFPRENE® 54R300A66/CT NEUTRO

Typical mechanical properties

Stress at 100% elongation	1.9 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	2.8 MPa	ISO 527-1/-2 or ISO 37
Stress at break	3.9 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	540 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	68	ISO 48-4 / ISO 868

Other properties

Density	1030 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------