



Ryton® XE5030BL

polyphenylene sulfide alloy

Ryton® XE5030BL 30% glass fiber reinforced polyphenylene sulfide alloy compound provides high ductility and impact resistance along with good thermal stability.

General

Material Status	• Commercial: Active	
Availability	• Asia Pacific • Europe	• Latin America • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Features	• Ductile • Good Thermal Stability	• High Impact Resistance
Uses	• Industrial Applications	
RoHS Compliance	• RoHS Compliant	
Appearance	• Black	
Forms	• Pellets	

Physical

	Typical Value	Unit	Test method
Density / Specific Gravity	1.51		ASTM D792
Molding Shrinkage			
Flow : 3.20 mm	0.20	%	
Across Flow : 3.20 mm	0.60	%	
Water Absorption (24 hr, 23°C)	0.050	%	ASTM D570

Mechanical

	Typical Value	Unit	Test method
Tensile Strength			
--	131	MPa	ASTM D638
--	135	MPa	ISO 527-2
Tensile Elongation (Break)	2.0	%	ASTM D638 ISO 527-2
Flexural Modulus			
--	8960	MPa	ASTM D790
--	9000	MPa	ISO 178
Flexural Strength			
--	193	MPa	ASTM D790
--	200	MPa	ISO 178
Compressive Strength	210	MPa	ASTM D695
Poisson's Ratio	0.38		ISO 527

Ryton® XE5030BL

polyphenylene sulfide alloy

Impact	Typical Value	Unit	Test method
Notched Izod Impact			
3.18 mm	96	J/m	ASTM D256
--	9.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact			
3.18 mm	690	J/m	ASTM D4812
--	45	kJ/m ²	ISO 180
Hardness	Typical Value	Unit	Test method
Rockwell Hardness			ASTM D785
M-Scale	86		
R-Scale	110		
Thermal	Typical Value	Unit	Test method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed	250	°C	
CLTE			ASTM E831
Flow : -50 to 50°C	2.0E-5	cm/cm/°C	
Flow : 100 to 200°C	1.0E-5	cm/cm/°C	
Transverse : -50 to 50°C	5.5E-5	cm/cm/°C	
Transverse : 100 to 200°C	9.0E-5	cm/cm/°C	
Thermal Conductivity	0.27	W/m/K	
UL Temperature Rating	130	°C	UL 746B
Electrical	Typical Value	Unit	Test method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
25°C, 1 kHz	3.80		
25°C, 1 MHz	3.70		
Dissipation Factor			ASTM D150
25°C, 1 kHz	3.0E-3		
25°C, 1 MHz	9.0E-3		
Arc Resistance	124	sec	ASTM D495
Comparative Tracking Index (CTI)	100	V	UL 746A
Insulation Resistance ¹ (90°C)	1.0E+11	ohms	

Ryton® XE5030BL

polyphenylene sulfide alloy

Flammability	Typical Value	Unit	Test method
Flame Rating (1.6 mm)	V-0		UL 94
Oxygen Index	34	%	ASTM D2863

Notes

Typical properties: these are not to be construed as specifications.

¹ 95%RH, 48 hr



Progress beyond

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2022 Solvay Specialty Polymers. All rights reserved.