

Moplen HP560X

更多资料请联系
18816996168



Polypropylene, Homopolymer

Product Description

Moplen HP560X is a polypropylene homopolymer used for extrusion applications. Moplen HP560X has a very high melt flow rate, a very narrow molecular weight distribution and is in pelletized form. Moplen HP560X is produced using a non-phthalate Ziegler/Natta catalyst and is used for the production of meltblown nonwovens with outstanding barrier/filtration properties. Moplen HP560X is also used for compounding applications.

Regulatory Status

For regulatory compliance information, see Moplen HP560X [Product Stewardship Bulletin \(PSB\) and Safety Data Sheet \(SDS\)](#).

This grade is not intended for medical and pharmaceutical applications.

| | |
|--------------------------|---|
| Status | Commercial: Active |
| Availability | Africa-Middle East; Europe |
| Application | Absorption & Filtration; Colour Concentrates; Hygiene Nonwoven; Nonwovens; Wipes/Tissues |
| Market | Compounding; Textile |
| Processing Method | Compounding; Continuous Filament/Spinning; Fibers; Melt Blown |
| Attribute | Controlled Rheology; Extremely High Flow; Homopolymer; Narrow Molecular Weight Distribution |

| Typical Properties | Nominal Value | Units | Test Method |
|----------------------------------|---------------|----------|-------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 800 | g/10 min | ISO 1133-1 |

Notes

These are typical property values not to be construed as specification limits.

Conveying:

Conveying equipment should be designed to prevent production and accumulation of fines and dust particles that are contained in polymer resins. These particles can under certain conditions pose an explosion hazard. Conveying systems should be grounded, equipped with adequate filters and regularly inspected for leaks.

Storage:

The resin is packed in 25 kg bags, octabins or bulk containers protecting it from contamination. If it is stored under certain conditions, i. e. if there are large fluctuations in ambient temperature and the atmospheric humidity is high, moisture may condense inside the packaging. Under these circumstances, it is recommended to dry the resin before use. Unfavorable storage conditions may also intensify the resin's slight characteristic odor.

Resin should be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Higher storage temperatures may reduce the storage time.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors of the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. This information does not remove the obligation of the customer to inspect the material on arrival and notify us of any faults immediately. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.