

# NORYL GTX™ RESIN GTX944

REGION EUROPE

## DESCRIPTION

NORYL GTX944 resin is a non-reinforced alloy of Polyphenylene Ether (PPE) + Polyamide (PA). This injection moldable grade exhibits high heat resistance along with improved processability and increased impact performance. NORYL GTX944 resin may be an excellent candidate for Firefighter Helmet applications.

GENERAL INFORMATION	
Features	Chemical Resistance, Hydrolytic Stability, Low Warpage, Low Shrinkage, Low Moisture Absorption, Low Specific Gravity, Dimensional stability, High stiffness/Strength, High temperature resistance, Impact resistant, No PFAS intentionally added
Fillers	Unreinforced
Polymer Types	Polyphenylene Ether + PA (PPE+Nylon)
Processing Techniques	Injection Molding

INDUSTRY	SUB INDUSTRY
Building and Construction	Building Component
Electrical and Electronics	Electronic Components

## TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL <sup>(1)</sup></b>			
Tensile Stress, yld, Type I, 50 mm/min	50	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	45	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 50 mm/min	1900	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	75	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	1950	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	3.5	%	ISO 527
Tensile Strain, break, 50 mm/min	50	%	ISO 527
Tensile Modulus, 1 mm/min	2000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	75	MPa	ISO 178
Flexural Modulus, 2 mm/min	1900	MPa	ISO 178
Ball Indentation Hardness, H358/30	75	MPa	ISO 2039-1
<b>IMPACT <sup>(1)</sup></b>			
Izod Impact, notched, 23°C	680	J/m	ASTM D256
Izod Impact, notched, -30°C	280	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	55	J	ASTM D3763
Izod Impact, notched 80*10*4 +23°C	55	kJ/m <sup>2</sup>	ISO 180/1A

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Izod Impact, notched 80*10*4 -20°C	25	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	25	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	55	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	25	kJ/m <sup>2</sup>	ISO 179/1eA
<b>THERMAL <sup>(1)</sup></b>			
Vicat Softening Temp, Rate B/50	180	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	185	°C	ASTM D648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	1.E-04	1/°C	ASTM E831
Thermal Conductivity	0.24	W/m.°C	ISO 8302
CTE, 23°C to 60°C, flow	9.E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	9.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	240	°C	ISO 306
Vicat Softening Temp, Rate B/50	180	°C	ISO 306
Vicat Softening Temp, Rate B/120	185	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	175	°C	ISO 75/Be
<b>PHYSICAL <sup>(1)</sup></b>			
Specific Gravity	1.08	-	ASTM D792
Mold Shrinkage on Tensile Bar, flow <sup>(2)</sup>	1.4 – 1.8	%	SABIC method
Mold Shrinkage, flow, 3.2 mm <sup>(2)</sup>	1.4 – 1.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm <sup>(2)</sup>	1.1 – 1.4	%	SABIC method
Melt Flow Rate, 280°C/5.0 kgf	12.5	g/10 min	ASTM D1238
Density	1.07	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/saturated)	3.5	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	1.2	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	12	cm <sup>3</sup> /10 min	ISO 1133
<b>ELECTRICAL <sup>(1)</sup></b>			
Volume Resistivity	2.2E+13	Ω.cm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	20	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.072	-	IEC 60250
Dissipation Factor, 1 MHz	0.024	-	IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Relative Permittivity, 50/60 Hz	3.5	-	IEC 60250
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Compliant, 94HB Flame Class Rating	1.6	mm	UL 94 by SABIC-IP
Oxygen Index (LOI)	21	%	ISO 4589
<b>INJECTION MOLDING <sup>(3)</sup></b>			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 3	Hrs	
Maximum Moisture Content	0.07	%	
Melt Temperature	290 – 320	°C	
Nozzle Temperature	280 – 310	°C	
Front - Zone 3 Temperature	290 – 320	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Middle - Zone 2 Temperature	280 – 300	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	80 – 120	°C	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.