

**25.10.2018**

## Specification

### Luran® S 703NT BK901510

Property name	Norm	Measuring Conditions	Limits	Unit
Vicat softening temperature	ISO 306	method B 50	min. 85	°C
MVR	ISO 1133	220°C, 10 kg; 4h 80°C predrying	2,0 - 13,0	cm <sup>3</sup> /10min
Charpy notched impact strength	ISO 179-1/1eA	23°C	min. 4	kJ/m <sup>2</sup>

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements.

Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.