

Xenoy* Resin CL100B

Europe-Africa-Middle East: COMMERCIAL

XENYOY CL100B has been specifically developed to obtain good low temperature impact strength, excellent UV stability and resistance to occasional solvent and gasoline contact. XENYOY CL100B is particularly suited for unpainted exterior automotive body components. This grade is a CL100 without release.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Taber Abrasion, CS-17, 1 kg	30	mg/1000cy	SABIC Method
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	75	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
Hardness, H358/30	96	MPa	ISO 2039-1
IMPACT	Value	Unit	Standard
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	46	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	21	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	50	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, 23°C	30	kJ/m ²	ISO 179/2C
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	35	kJ/m ²	ISO 179/1eA
Charpy Impact, notched, -20°C	10	kJ/m ²	ISO 179/2C
Charpy Impact, notched, -30°C	10	kJ/m ²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL	Value	Unit	Standard
Thermal Conductivity	0.18	W/m-°C	ISO 8302
CTE, 23°C to 80°C, flow	9.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	1.E-04	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	150	°C	ISO 306
Vicat Softening Temp, Rate B/50	125	°C	ISO 306
Vicat Softening Temp, Rate B/120	129	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	110	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	90	°C	ISO 75/Ae
PHYSICAL	Value	Unit	Standard
Mold Shrinkage on Tensile Bar, flow (2)	0.7 - 1	%	SABIC Method
Mold Shrinkage on Tensile Bar, xflow (2)	0.7 - 1	%	SABIC Method
Density	1.22	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.5	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 250°C/5.0 kg	14	cm ³ /10 min	ISO 1133

ELECTRICAL	Value	Unit	Standard
Volume Resistivity	>1.E+14	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, shorttime, 1.0mm	18	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	IEC 60243-1
Relative Permittivity, 50/60 Hz	3.3	-	IEC 60250
Relative Permittivity, 1 MHz	3.3	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.002	-	IEC 60250
Dissipation Factor, 1 MHz	0.02	-	IEC 60250
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Recognized, 94HB Flame Class Rating (3)	1.5	mm	UL 94
UL Recognized, 94HB Flame Class Rating 2nd value (3)	3	mm	UL 94


Source GMD, last updated:12/14/1999

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	90 - 100	°C
Drying Time	2 - 4	hrs
Maximum Moisture Content	0.02	%
Melt Temperature	255 - 270	°C
Nozzle Temperature	250 - 265	°C
Front - Zone 3 Temperature	250 - 270	°C
Middle - Zone 2 Temperature	240 - 265	°C
Rear - Zone 1 Temperature	230 - 250	°C
Hopper Temperature	40 - 60	°C
Mold Temperature	60 - 80	°C

Source GMD, last updated:12/14/1999

CALCULATED FLOW LENGTH INDICATION
Moldflow® Radial Flow Analysis
Valox® V3001MC
Melt Temperature : 260°C
Mold Temperature : 70°C



Note: Technical support is recommended if Gate Pressure is greater than 80 MPa. Contact your local representative.
 © Moldflow is a registered trademark of the Moldflow Corporation.

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

(1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.

(2) Only typical data for selection purposes. Not to be used for part or tool design.

(3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

(4) Internal measurements according to UL standards.

Disclaimer : All information, recommendation or advice given by SABIC Innovative Plastics, or any of its subsidiaries, affiliates or authorized representatives, whether written or oral, is given in good faith, to the best of its knowledge and based on current procedures in effect. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is beyond the control of SABIC Innovative Plastics Company, its subsidiaries and affiliates, such use is in the exclusive responsibility of the user. SABIC Innovative Plastics Company, its subsidiaries and affiliates cannot be held responsible respectively liable for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliated companies, nor to grant the right to file for any patent protection.

* Xenoy is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company. All rights reserved