





SABIC NORYL V03505 PPE+HIPS (Europe-Africa-Middle East)




Categories: [Polymer](#); [Thermoplastic](#); [Polyphenylene Ether/PPQ](#); [Polystyrene \(PS\)](#)




Material Notes: Noryl* V03505 is a 35% milled fiber reinforced, injection moldable grade. Designed for good dimensional stability and low warpage, this resin also uses non-chlorinated, non-brominated FR additives to achieve a V0 UL94 rating at 2.0 mm. Noryl V03505 is may be an excellent material candidate for application requiring low warpage and flame resistance.

Vendors: No vendors are listed for this material. Please [click here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	ASTM D792
Density	1.35 g/cc	0.0488 lb/in ³	ISO 1183
Moisture Absorption	0.0600 %	0.0600 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.20 %	0.20 %	ISO 62
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm @Thickness 3.20 mm	0.0030 - 0.0050 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	49 g/10 min @Load 5.00 kg, Temperature 300 °C	49 g/10 min @Load 11.0 lb, Temperature 572 °F	ASTM D1238
Melt Index of Compound 	15 g/10 min @Load 3.80 kg, Temperature 280 °C	15 g/10 min @Load 8.38 lb, Temperature 536 °F	MVR [cm ³ /10 min]; ISO 1133
	24 g/10 min @Load 5.00 kg, Temperature 280 °C	24 g/10 min @Load 11.0 lb, Temperature 536 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	147 MPa	21300 psi	ISO 2039-1
Tensile Strength at Break	50.0 MPa	7250 psi	5 mm/min; ISO 527
	57.0 MPa	8270 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	50.0 MPa	7250 psi	5 mm/min; ISO 527
	59.0 MPa	8560 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	4.0 %	4.0 %	Type I, 5 mm/min; ASTM D638
	4.0 %	4.0 %	5 mm/min; ISO 527
Elongation at Yield	3.0 %	3.0 %	Type I, 5 mm/min; ASTM D638
	3.0 %	3.0 %	5 mm/min; ISO 527
Tensile Modulus	4.40 GPa	638 ksi	5 mm/min; ASTM D638
	5.00 GPa	725 ksi	1 mm/min; ISO 527
Flexural Strength	95.0 MPa	13800 psi	2 mm/min; ISO 178
Flexural Yield Strength	100 MPa	14500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	4.30 GPa	624 ksi	1.3 mm/min, 50 mm span; ASTM D790
	4.70 GPa	682 ksi	2 mm/min; ISO 178
Izod Impact, Notched 	0.350 J/cm	0.656 ft-lb/in	ASTM D256
	0.350 J/cm @Temperature -30.0 °C	0.656 ft-lb/in @Temperature -22.0 °F	ASTM D256
Izod Impact, Unnotched (ISO) 	26.0 kJ/m ²	12.4 ft-lb/in ²	80*10*4; ISO 180/1U
	24.0 kJ/m ² @Temperature -30.0 °C	11.4 ft-lb/in ² @Temperature -22.0 °F	80*10*4; ISO 180/1U
Charpy Impact Unnotched 	3.00 J/cm ²	14.3 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eU
	3.00 J/cm ² @Temperature -30.0 °C	14.3 ft-lb/in ² @Temperature -22.0 °F	Edgew 80*10*4 sp=62mm; ISO 179/1eU
Dart Drop, Total Energy	13.0 J	9.59 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093
Dielectric Constant 	3.1	3.1	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.2	3.2	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength 	15.0 kV/mm @Thickness 3.20 mm	381 kV/in @Thickness 0.126 in	in oil; IEC 60243-1
	26.0 kV/mm @Thickness 1.60 mm	660 kV/in @Thickness 0.0630 in	in oil; IEC 60243-1
	33.0 kV/mm @Thickness 0.800 mm	838 kV/in @Thickness 0.0315 in	in oil; IEC 60243-1
Dissipation Factor 	0.0030	0.0030	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

	0.0060 @Frequency 50.0 - 60.0 Hz	0.0060 @Frequency 50.0 - 60.0 Hz	IEC 60250
Thermal Properties			
CTE, linear, Parallel to Flow 	Metric	English	Comments
	40.0 µm/m-°C @Temperature 23.0 - 80.0 °C	22.2 µin/in-°F @Temperature 73.4 - 176 °F	ISO 11359-2
CTE, linear, Transverse to Flow 	50.0 µm/m-°C @Temperature -40.0 - 40.0 °C	27.8 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
	50.0 µm/m-°C @Temperature 23.0 - 80.0 °C	27.8 µin/in-°F @Temperature 73.4 - 176 °F	ISO 11359-2
Thermal Conductivity	0.280 W/m-K	1.94 BTU-in/hr-ft²-°F	ISO 8302
Hot Ball Pressure Test	<= 105 °C	<= 221 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	105 °C	221 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
	91.0 °C @Thickness 3.20 mm	196 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	110 °C	230 °F	Rate B/50; ISO 306
	115 °C	239 °F	Rate B/50; ASTM D1525
	120 °C	248 °F	Rate A/50; ISO 306
	120 °C	248 °F	Rate B/120; ISO 306
UL RTI, Electrical	50.0 °C	122 °F	UL 746B
UL RTI, Mechanical with Impact	50.0 °C	122 °F	UL 746B
UL RTI, Mechanical without Impact	50.0 °C	122 °F	UL 746B
Flammability, UL94 	V-1 @Thickness 1.50 mm	V-1 @Thickness 0.0591 in	UL 94
	V-0 @Thickness 2.00 mm	V-0 @Thickness 0.0787 in	UL 94
Oxygen Index	34 %	34 %	ISO 4589
Glow Wire Flammability Index	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 3.20 mm	@Thickness 0.126 in	

Descriptive Properties

Ball Pressure Test, 75°C +/- 2°C	PASSES	IEC 60695-10-2
----------------------------------	--------	----------------

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's [terms of use](#) regarding this information. [Click here](#) to view all the property values for this datasheet as they were originally entered into MatWeb.