

Product Information**Product Characteristics**

- 92 Shore A
- Injection and Extrusion Molding
- High Microbial Resistance

Properties	Test Method	Typical Values
Physical Properties¹		
Shore Hardness A Scale	DIN53505	92
Shore Hardness D Scale	DIN53505	40
Mold Shrinkage	D995	0.004
Specific Gravity	DIN53479	1.14
Mechanical Properties¹		
Tensile Strength	DIN53504	5802 psi
Ultimate Elongation	DIN53504	500%
100% Tensile Modulus	DIN53504	1450 psi
300% Tensile Modulus	DIN53504	2901 psi
Tear Strength	DIN53515	371 pli
Abrasion Resistance	DIN53516	35 mm
Compression Set/ 70h @ 23C	DIN53517	25%
Compression Set/ 24h @ 70C	DIN53517	40%

¹ Typical Properties; not to be construed as specifications. The data is intended as a general guideline only and does not necessarily represent the results that may be obtained otherwise.

Irogran® is a registered trademark of Huntsman Corporation and is distributed by Calsak Corporation

Issued 9-1-13