

# Stanyl® TE250F6

## PA46-GF30 FR(17)

30% Glass Reinforced, Heat Stabilized, Flame Retardant

Print Date: 2021-09-16

Stanyl® TE250F6 is an electro-friendly & flame-retarded high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

Properties	Typical Data	Unit	Test Method
<b>Rheological properties</b>			
	dry / cond		
Molding shrinkage [parallel]	0.4 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.1 / *	%	Sim. to ISO 294-4
<b>Mechanical properties</b>			
	dry / cond		
Tensile modulus	12000 / 8000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	7500 / -	MPa	ISO 527-1/-2
Tensile modulus (160°C)	6200	MPa	ISO 527-1/-2
Stress at break	180 / 120	MPa	ISO 527-1/-2
Stress at break (120°C)	105 / -	MPa	ISO 527-1/-2
Stress at break (160°C)	95	MPa	ISO 527-1/-2
Strain at break	2.5 / 3.5	%	ISO 527-1/-2
Strain at break (120°C)	4 / -	%	ISO 527-1/-2
Strain at break (160°C)	4	%	ISO 527-1/-2
Flexural modulus	11000 / 7300	MPa	ISO 178
Flexural modulus (120°C)	6500	MPa	ISO 178
Flexural modulus (160°C)	5000	MPa	ISO 178
Flexural strength	260 / 190	MPa	ISO 178
Flexural strength (120°C)	170	MPa	ISO 178
Flexural strength (160°C)	140	MPa	ISO 178
Charpy impact strength (+23°C)	60 / 60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	50 / 50	kJ/m <sup>2</sup>	ISO 179/1eU

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2021. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.



**DSM**

BRIGHT SCIENCE. BRIGHTER LIVING.

Properties	Typical Data	Unit	Test Method
Charpy notched impact strength (+23°C)	11 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	10 / 10	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength (+23°C)	11 / 11	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength (-40°C)	11 / 11	kJ/m <sup>2</sup>	ISO 180/1A

**Thermal properties**

dry / cond

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	290 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.25 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.55 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Relative Temperature Index - electrical	140	°C	UL746B
RTI electrical (Thickness (1) tested)	0.75	mm	UL746B
Thermal Index 5000 hrs	163	°C	IEC 60216/ISO 527-1/-2

**Electrical properties**

dry / cond

Volume resistivity	1E13 / 1E8	Ohm*m	IEC 62631-3-1
Electric strength	30 / 20	kV/mm	IEC 60243-1
Comparative tracking index	225 / -	V	IEC 60112
Relative permittivity (100Hz)	4.3 / 10	-	IEC 62631-2-1
Relative permittivity (1 MHz)	4 / 4.5	-	IEC 62631-2-1
Relative permittivity (1GHz)	3.6 / 3.8	-	IEC 60250

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2021. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.



**DSM**

BRIGHT SCIENCE. BRIGHTER LIVING.

## Property Data

# Stanyl<sup>®</sup> TE250F6

Print Date: 2021-09-16

Properties	Typical Data	Unit	Test Method
<b>Other properties</b>	<b>dry / cond</b>		
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1670 / -	kg/m <sup>3</sup>	ISO 1183

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2021. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

