

# Terlux 2812

Methyl Methacrylate Acrylonitrile Butadiene Styrene (MABS)

## TECHNICAL DATASHEET

### DESCRIPTION

Terlux® 2812 is an easy-flowing injection molding grade based on a MABS polymer. Terlux® 2812 offers an unique combination of properties, such as a balanced stiffness/toughness ratio and the high transparency well known in SAN molding compositions.

### FEATURES

- Excellent transparency
- Good resistance to chemicals
- Good Stiffness and surface finish
- High impact strength
- Easy-flow grade

### APPLICATIONS

- Cosmetic packaging
- Homeware
- Housings
- Toys, sport and leisure

Property, Test Condition	Standard	Unit	Values
<b>Rheological Properties</b>			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm <sup>3</sup> /10 min	8
Melt Volume Rate, 220 °C/21.6 kg	ISO 1133	cm <sup>3</sup> /10 min	45
<b>Mechanical Properties</b>			
Charpy Notched Impact Strength, 23° C	ISO 179	kJ/m <sup>2</sup>	5
Charpy Notched Impact Strength, -30° C	ISO 179	kJ/m <sup>2</sup>	2
Charpy Unnotched, 23° C	ISO 179	kJ/m <sup>2</sup>	110
Charpy Unnotched, -30° C	ISO 179	kJ/m <sup>2</sup>	70
Tensile Stress at Yield, 23° C	ISO 527	MPa	42
Tensile Strain at Yield, 23° C	ISO 527	%	4
Tensile Modulus	ISO 527	MPa	1900
Nominal Strain at Break, 23 °C	ISO 527	%	20
Flexural Strength	ISO 178	MPa	60
Hardness, Ball Indentation	ISO 2039-1	MPa	75
<b>Thermal Properties</b>			
Vicat Softening Temperature VST/B/50 (50N, 50°C/h)	ISO 306	°C	87
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	87

# Terlux 2812

Methyl Methacrylate Acrylonitrile Butadiene Styrene (MABS)

## TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	93
Coefficient of Linear Thermal Expansion	ISO 11359	10 <sup>-6</sup> /°C	80 - 110
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
<b>Electrical Properties</b>			
Dielectric Constant (100 Hz)	IEC 60250	-	3
Dissipation Factor (100 Hz)	IEC 60250	10 <sup>-4</sup>	160
Dissipation Factor (1 MHz)	IEC 60250	10 <sup>-4</sup>	130
Volume Resistivity	IEC 60093	Ohm*m	1E14
Surface Resistivity	IEC 60093	Ohm	1E15
<b>Optical Properties</b>			
Refractive Index, Sodium D Line	ISO 489	-	1.540
<b>Other Properties</b>			
Density	ISO 1183	kg/m <sup>3</sup>	1080
Water Absorption, Saturated at 23°C	ISO 62	%	0.7
<b>Processing</b>			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	230 - 260
Mold Temperature Range	ISO 294	°C	50 - 75
Injection Velocity	ISO 294	mm/s	200
Drying Temperature		°C	70
Drying Time		h	2

Typical values for uncolored products

## PROCESSING

Terlux is primarily processed through injection molding but any process suitable for thermoplastic molding compositions may also be used.

**DISCLAIMER**

The above information is provided in good faith. INEOS Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, INEOS Styrolution MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.