

Polypropylene H734-52RNA

Sub-group:

Homopolymer

Description:

BRASKEM H734-52RNA Polypropylene Resin is a homopolymer developed for thin wall, high speed injection molding. BRASKEM H734-52RNA Polypropylene Resin is a high flow homopolymer with a good balance of physical properties. BRASKEM H734- 52RNA Polypropylene Resin contains a very efficient antistatic package and offers good transparency when required. BRASKEM H734-52RNA Polypropylene Resin is designed and formulated to allow for very easy processing, short cycle times, low shrinkage, minimal warpage and good part dimensional stability.

Applications:

- Thin wall food packaging
- Thin wall cosmetic packaging
- Housewares
- Appliances
- Caps & closures
- Videocassette boxes
- Office accessories & pens

Process:

Injection molding.

Properties:

Physical Properties ^{a)}	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.900 g/cm ³	0.900 g/cm ³	ISO 1183
Melt Mass-Flow Rate (230°C/2.16 kg)	52 g/10 min	52 g/10 min	ISO 1133
Flexural Modulus (23°C)	246500 psi	1700 MPa	ISO 178
Tensile Stress at Yield	5370 psi	37 MPa	ISO 527-2
Tensile Strain at Yield	9 %	9 %	ISO 527-2
Charpy Notched Impact Strength (23°C)	1.2 ft·lb/in ²	2.5 kJ/m ²	ISO 179/1eA
Heat Deflection Temperature (0.45 MPa)	221 °F	105 °C	ISO 75-2/B
Vicat Softening Temperature (10N)	306 °F	152 °C	ISO 306/A

a) These are typical properties from injection molding specimen according to ISO 294 only and are not to be construed as specifications. Users should confirm results by their own tests.

Processing conditions:

BRASKEM H734-52RNA is easy to process with injection molding equipment with conditions depending on the type of injection molding conversion technology applied. Recommended melt temperature range for injection molding from 210 to 260°C.

Storage:

Recommended storage is a cool, dry place protected from direct sunlight for maximum of 24 months after production.

Customer Notice:

Braskem strongly encourages its customers to review both their manufacturing processes and their applications of Braskem products from the standpoint of human health and environmental quality to ensure

that Braskem products are not used in ways for which they are not intended or tested. Braskem personnel are available to answer your questions and to provide reasonable technical support. Braskem product literature, including safety data sheets, should be consulted prior to use of Braskem products. Current safety data sheets are available from Braskem.

Disclaimer:

- Braskem Netherlands B.V. or any of its affiliates assumes no liability on the suitability of the product as described in this document for any intended use in any application unless separately agreed in a contract. All warranties or merchantability or fitness for a particular purpose are expressly excluded.
- Braskem Netherlands B.V. does not support the use of the product as described in this document in any medical application regardless of the Medical Device Classification (Directive 93/42/EEC). The use of this product into any medical applications regardless of classification or intended use, requires written approval from Braskem Netherlands B.V..
- Braskem Netherlands B.V. assumes no obligation or liability for the information provided in this document.

Notice:

- Braskem strongly recommends before use, to consult the Material Safety Data Sheet
- Inspire® is a trademark of Braskem SA
- Braskem Netherlands B.V. registration details are: Braskem Netherlands B.V., Weena 240 / Tower C 9th Floor, 3012 NJ Rotterdam, The Netherlands Commercial Court Rotterdam No.: 24401995 Managing Directors: : Hans-Jürgen Buchmann; Alexander van Veen; Axel Maigatter. VAT Number: NL817054716B01
- If products are described as “experimental” or “developmental”:
 1. Product specification may not be fully determined;
 2. Analysis of hazards and caution in handling and use are required;
 3. There is a greater potential for Braskem to change specifications and/or discontinue production, and;
 4. Although Braskem may from time to time provide samples of such products, Braskem is not obliged to supply or otherwise commercialize such products for any use or application whatsoever.

For regulatory information, please contact polymer.compliance-europe@braskem.com. For other requests, please contact Braskem via e-mail address: europe.polypropylene@braskem.com.

This document is intended for use in Europe, published 14th August 2019.