MAFILL CR CM 5144

Polypropylene Ravago Manufacturing Americas

Product Description

10% Mineral Compounded



Property	Test Method	Value	Units
Physical			
Melt Flow Rate	ISO 1133	10	g/10 min
Filler Content	ISO 3451	10	%
Specific Gravity	ISO 1183	0.97	g/cm ³
Mechanical			
Strength at Yield	ISO 527	21	MPa
Flexural Modulus	ISO 178	1100	Мра
Notched Izod Impact, 23C	ISO 180	5	kJ/m2

Ravago Manufacturing Americas disclaimer statement:

The technical information, suggested uses, and applications presented, are made without charge and are believed to be reliable; however, Ravago Manufacturing Americas disclaims responsibility for reliance on, and results of use of, this information. The data listed herein falls within the nominal range of product properties but should not be used to establish specification limits or used alone as a basis for design. This information is not intended as a warranty of any kind. Users must make their own representative test and assume all risks of use, whether the product is used alone or in combination with other materials. Ravago Manufacturing Americas assumes no obligation or liability for any advice furnished or results obtained with respect to the product, nor for use of the product in infringement of any patent. ALL WARRANTIES, EXPRESSED OR IMPLIED, OF MERCHANTABILITY, AND FITNESS FOR A PARTICULAR PURPOSE OR USE ARE EXCLUDED AND DISCLAIMED. The foregoing limitation of remedy and exclusion of liability is reflected in, and is part of, the consideration for the price charged for the product.

All data displayed herein has been obtained via testing of injected molded specimens of natural color. Pigmentation may affect certain properties to various degrees.

≠ Shrinkage data are general guidelines and are only intended to allow comparison to other materials. They should not be used as the sole source of information for generating core and cavity mold dimensions.

Ravago Manufacturing Americas

1900 Summit Tower Blvd., Suite 900 Orlando, FL 32810 Tel: 1-800-459-7009

www.ravago.com