

TECHNICAL DATA SHEET

EVOPRENE G 969

TECHNICAL PROPERTIES

Primary Properties	Unit	Temperature	Nominal Value	Test Method
Hardness Shore A	Deg	23 °C	67	ISO 868
Specific Gravity	g/cm ³	23 °C	0.90	ISO 2781
Flow Rating	kg/cm ²	180 °C	12	AG Internal Test
Tensile Strength	MPa	23 °C	8.2	ISO 37
Elongation at Break	%	23 °C	500	ISO 37
Modulus at 100% elongation	MPa	23 °C	3.0	ISO 37
Modulus at 300% elongation	MPa	23 °C	4.3	ISO 37
Tear Strength	kN/m	23 °C	37	ISO 6383
Abrasion Resistance	Cu.mm loss	23 °C	165	ISO 53516

Compression Set	Unit	Temperature	Nominal Value	Test Method
72 hours	%	23 °C	18	ISO 815
22 hours	%	70 °C	36	ISO 815
22 hours	%	100 °C	52	ISO 815

Air-Oven Ageing 14 days @ 125 °C	Unit	Temperature	Nominal Value	Test Method
Hardness Change	Deg		+1	ISO 188
Retained Tensile Strength	%		113	ISO 188
Retained Elongation at Break	%		118	ISO 188

Note: the above tests are carried out on injection moulded test pieces

Customer shall not copy, reverse engineer, analyse or have analysed Alphagary / Mexichem Specialty Compounds materials or allow others to do so.

Although Alphagary / Mexichem Specialty Compounds believes these data are accurate as of the date hereof, they are provided for informational purposes only. It cannot be assumed that these data cover all uses, applications or conditions in connection with this material. Accordingly, Alphagary / Mexichem Specialty Compounds makes no warranty, expressed or implied that the product conforms to these data. Each customer or user of Alphagary / Mexichem Specialty Compounds materials is solely responsible for determining the suitability of the material(s) selected for the intended application. Each customer or user must conduct its own studies and gain all necessary approvals and certifications as required for the intended finished product.