

THERMOLAST® K TF9AAA (Series: FC/HE/tl)

Thermoplastic Elastomer

KRAIBURG TPE

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

The FC/HE/tl Series is your material solution for applications with food contact, providing excellent resilience properties. The series is available in translucent colors.

Typical applications

- Closures
- Flexible Connections
- Household articles
- Membranes
- Packaging (for food and careproducts)
- Seals
- Valves

Material advantages

- Applications with food contact
- Easy coloring (compounds in natural colors)
- EN71/3
- Excellent mechanical properties
- FDA - Code of Federal Regulations (CFR), Title 21
- Halogen-free
- High resilience
- Perfect adhesion to PP
- Regulation (EU) No 10/2011

General

Material Status	• Commercial: Active		
Literature ¹	• Technical Datasheet (English)		
Search for UL Yellow Card	• KRAIBURG TPE • THERMOLAST® K		
Availability	• Africa & Middle East • Europe	• Latin America • North America	
Features	• Food Contact Acceptable • Good Adhesion	• Halogen Free • Resilient	
Uses	• Closures • Connectors • Food Packaging	• Household Goods • Membranes • Non-specific Food Applications	• Packaging • Seals • Valves/Valve Parts
Agency Ratings	• EN 71-3	• EU 10/2011	• FDA Food Contact, Unspecified Rating
Appearance	• Translucent		
Processing Method	• Extrusion	• Injection Molding	

Physical	Nominal Value Unit	Test Method
Density	0.890 g/cm ³	ISO 1183
Elastomers	Nominal Value Unit	Test Method
Tensile Stress ³ (Break)	20.5 MPa	ISO 37
Tensile Elongation ³ (Break)	700 %	ISO 37
Tear Strength ⁴	30.0 kN/m	ISO 34-1
Compression Set ⁵		ISO 815
23°C, 72 hr	29 %	
70°C, 24 hr	41 %	
100°C, 24 hr	70 %	
Hardness	Nominal Value Unit	Test Method
Shore Hardness (Shore A)	83	ISO 7619



THERMOLAST® K TF9AAA (Series: FC/HE/tl)

Thermoplastic Elastomer

KRAIBURG TPE

PROSPECTOR®

www.ulprospector.com

Injection	Nominal Value Unit
Drying Temperature	60 to 80 °C
Drying Time	2.0 to 4.0 hr
Rear Temperature	180 °C
Middle Temperature	200 °C
Front Temperature	220 °C
Mold Temperature	25 to 40 °C
Injection Pressure	20.0 to 100 MPa
Back Pressure	2.00 to 10.0 MPa

Extrusion	Nominal Value Unit
Drying Temperature	60 to 80 °C
Drying Time	2.0 to 4.0 hr
Cylinder Zone 1 Temp.	160 °C
Cylinder Zone 2 Temp.	180 °C
Cylinder Zone 3 Temp.	200 °C
Die Temperature	200 to 230 °C
Screw L/D Ratio	25.0:1.0

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

³ Type S2, 200 mm/min

⁴ Method Bb, Angle (Nicked)

⁵ Method A



THERMOLAST® K TF9AAA (Series: FC/HE/tl)

Thermoplastic Elastomer

KRAIBURG TPE

PROSPECTOR®

www.ulprospector.com

Where to Buy

Supplier

KRAIBURG TPE

Duluth, GA USA

Telephone: 678-584-5020

Web: <http://www.kraiburgtpe.com/>

Distributor

Chase Plastic Services, Inc.

Chase Plastics Services is a North American distributor with representatives throughout the region. Please find your rep here: <http://www.chaseplastics.com/contact/locations>

Telephone: 800-232-4273

Web: <http://www.chaseplastics.com/>

Availability: North America

Lenorplastics Zug

Telephone: +41-41-798-02-11

Web: <https://www.lenorplastics.ch>

Availability: Switzerland

Plastoplan

Telephone: +43-1-25040-0

Web: <https://www.plastoplan.com/>

Availability: Austria, Hungary, Poland

