

Terlux HD 2802

Methyl Methacrylate Acrylonitrile Butadiene Styrene (MABS)

TECHNICAL DATASHEET

DESCRIPTION

Terlux® HD 2802 is a standard injection molding grade based on a MABS polymer. Terlux® HD 2802 offers an unique combination of properties, such as a balanced stiffness/toughness ratio and the high transparency well known in SAN molding compositions.

FEATURES

- Excellent transparency
- Good resistance to chemicals
- Good stiffness and surface finish
- High impact strength
- HD service package available

APPLICATIONS

- Medical devices

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	2
Melt Volume Rate, 220 °C/21.6 kg	ISO 1133	cm ³ /10 min	17
Mechanical Properties			
Charpy Notched Impact Strength, 23° C	ISO 179	kJ/m ²	5
Charpy Notched Impact Strength, -30° C	ISO 179	kJ/m ²	2
Charpy Unnotched, 23° C	ISO 179	kJ/m ²	120
Charpy Unnotched, -30° C	ISO 179	kJ/m ²	80
Tensile Stress at Yield, 23° C	ISO 527	MPa	48
Tensile Strain at Yield, 23° C	ISO 527	%	4
Tensile Modulus	ISO 527	MPa	2000
Tensile Creep Modulus (1000h)	ISO 899	MPa	1250
Nominal Strain at Break, 23 °C	ISO 527	%	12
Flexural Strength	ISO 178	MPa	70
Hardness, Ball Indentation	ISO 2039-1	MPa	70
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50°C/h)	ISO 306	°C	93

Terlux HD 2802

Methyl Methacrylate Acrylonitrile Butadiene Styrene (MABS)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Vicat Softening Temperature, VST/A/50 (10N, 50°C/h)	ISO 306	°C	105
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	90
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	94
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	80 - 110
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Dielectric Constant (100 Hz)	IEC 60250	-	2.9
Dissipation Factor (100 Hz)	IEC 60250	10 ⁻⁴	160
Dissipation Factor (1 MHz)	IEC 60250	10 ⁻⁴	140
Volume Resistivity	IEC 60093	Ohm*m	1E13
Surface Resistivity	IEC 60093	Ohm	1E15
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.540
Other Properties			
Density	ISO 1183	kg/m ³	1080
Bulk Density (with external lubricant)		kg/m ³	590
Water Absorption, Saturated at 23°C	ISO 62	%	0.7
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	230 - 260
Mold Temperature Range	ISO 294	°C	50 - 75
Injection Velocity	ISO 294	mm/s	200
Drying Temperature		°C	70
Drying Time		h	2

Typical values for uncolored products

SUPPLY FORM

Terlux® is supplied as lenticular and as cylindrical pellets. The bulk density is from about 0.55-0.65 g/cm³.

PROCESSING

Terlux is primarily processed through injection molding but any process suitable for thermoplastic molding compositions may also be used.

DISCLAIMER

The above information is provided in good faith. INEOS Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, INEOS Styrolution **MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.
