

Product Comparison

Technical Data

Product Description

VALOX™ Resin 508 - Europe 30% GR PBT+PC. Excellent mechanical and thermal performance. Non-flame retardant. Reduced warpage characteristics. Applications same as VALOX 420.

Generic PBT This data represents typical values that have been calculated from all products classified as: Generic PBT
This information is provided for comparative purposes only.

General	VALOX™ Resin 508 - Europe	Generic PBT
Manufacturer / Supplier	• SABIC	• Generic
Generic Symbol	• PBT	• PBT
Material Status	• Commercial: Active	• Commercial: Active
UL Yellow Card ¹	• E45329-236608	--
Search for UL Yellow Card	• SABIC • VALOX™ Resin	--
Availability	• Europe	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Uses	• Aerospace Applications • Appliances • Automotive Exterior Parts • Automotive Interior Parts • Automotive Lighting • Automotive Under the Hood • Construction Applications • Electrical Parts • Electrical/Electronic Applications • Electronic Displays • Heavy Transportation • Industrial Applications • Lawn & Garden Equipment • Lighting Applications • Material Handling • Medical/Healthcare Applications • Outdoor Applications • Water Management	--
Also Available In	• Asia Pacific • Latin America • North America	• Asia Pacific • Europe • Latin America • North America

Physical	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Density / Specific Gravity				
--	--	1.26 to 1.55	g/cm ³	ASTM D792
--	1.50	1.29 to 1.32	g/cm ³	ISO 1183
--	--	1.31	g/cm ³	ASTM D1505
Apparent (Bulk) Density	--	0.80 to 0.81	g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR)				
250°C/2.16 kg	--	8.0 to 56	g/10 min	ASTM D1238
250°C/2.16 kg	--	3.0 to 72	g/10 min	ISO 1133



Physical	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	8.0	3.7 to 52	cm³/10min	ISO 1133
Molding Shrinkage				
Flow	--	0.54 to 2.1	%	ASTM D955
Across Flow	--	0.99 to 2.0	%	ASTM D955
--	--	0.19 to 2.3	%	ISO 294-4
Across Flow ³	0.50 to 0.90	--	%	Internal Method
Flow ³	0.40 to 0.60	--	%	Internal Method
Water Absorption				
24 hr	--	0.050 to 0.11	%	ASTM D570
24 hr, 23°C	--	0.040 to 0.20	%	ISO 62
Saturation	--	0.20 to 0.50	%	ASTM D570
Saturation, 23°C	0.090	0.077 to 0.52	%	ISO 62
Equilibrium	--	0.070 to 0.090	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.060	0.054 to 0.27	%	ISO 62
Viscosity Number (Reduced Viscosity)	--	0.6 to 160.0	ml/g	ISO 1628
Viscosity Number	--	1.23 to 160	cm³/g	ISO 307
Intrinsic Viscosity	--	0.74 to 1.3	dl/g	
Mechanical	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Tensile Modulus				
--	--	2110 to 2860	MPa	ASTM D638
--	--	2100 to 2880	MPa	ISO 527-1
--	9000	--	MPa	ISO 527-1/1
Tensile Strength				
Yield	--	45.5 to 120	MPa	ASTM D638
Yield	--	38.4 to 61.7	MPa	ISO 527-2
Break	--	22.0 to 142	MPa	ASTM D638
Break	--	33.6 to 60.6	MPa	ISO 527-2
Break	115	--	MPa	ISO 527-2/5
--	--	44.4 to 60.4	MPa	ASTM D638
--	--	31.5 to 60.3	MPa	ISO 527-2
Tensile Elongation				
Yield	--	1.0 to 16	%	ASTM D638
Yield	--	1.8 to 11	%	ISO 527-2
Break	--	0.50 to 110	%	ASTM D638
Break	--	1.6 to 23	%	ISO 527-2
Break	2.0	--	%	ISO 527-2/5
Nominal Tensile Strain at Break				
	--	2.5 to 52	%	ISO 527-2
Tensile Creep Modulus				
				ISO 899-1
1 hr	--	2400	MPa	
1000 hr	--	1580	MPa	
Flexural Modulus				
--	--	1700 to 2980	MPa	ASTM D790
--	--	2090 to 2920	MPa	ISO 178
-- ⁴	8000	--	MPa	ISO 178



Mechanical	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Flexural Strength				
--	--	58.3 to 98.9	MPa	ASTM D790
--	--	8.00 to 113	MPa	ISO 178
-- 4, 5	170	--	MPa	ISO 178
Yield	--	74.6 to 85.8	MPa	ASTM D790
Break	--	2.00 to 205	MPa	ASTM D790
Compressive Strength	--	19.3 to 124	MPa	ASTM D695
Poisson's Ratio	--	0.38		ASTM E132
Coefficient of Friction	--	0.12 to 0.41		ASTM D1894
Taber Abrasion Resistance				
--	--	9.00 to 55.2	mg	ASTM D1044
1000 Cycles, 1000 g, CS-17 Wheel	50.0	--	mg	Internal Method
Impact	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Charpy Notched Impact Strength				
--	--	1.5 to 10	kJ/m ²	ISO 179
-30°C ⁶	6.0	--	kJ/m ²	ISO 179/1eA
23°C ⁶	7.0	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				
--	--	12 to 200	kJ/m ²	ISO 179
-30°C ⁶	45	--	kJ/m ²	ISO 179/1eU
23°C ⁶	45	--	kJ/m ²	ISO 179/1eU
Notched Izod Impact				
--	--	29 to 100	J/m	ASTM D256
--	--	2.0 to 11	kJ/m ²	ISO 180
-30°C ⁷	7.0	--	kJ/m ²	ISO 180/1A
23°C ⁷	8.0	--	kJ/m ²	ISO 180/1A
Notched Izod Impact (Area)	--	3.30 to 40.0	kJ/m ²	ASTM D256
Unnotched Izod Impact				
--	--	23 to 3200	J/m	ASTM D4812
--	--	24 to 150	kJ/m ²	ISO 180
-30°C ⁷	40	--	kJ/m ²	ISO 180/1U
23°C ⁷	45	--	kJ/m ²	ISO 180/1U
Instrumented Dart Impact				
--	--	2.00 to 61.4	J	ASTM D3763
--	--	3.20 to 120	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force	--	2240 to 5190	N	ISO 6603-2
Gardner Impact	--	36.0 to 43.0	J	ASTM D3029



Hardness	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Rockwell Hardness				
--	--	117 to 122		ASTM D785
--	--	71 to 125		ISO 2039-2
R-Scale	119	--		ISO 2039-2
Shore Hardness				
	--	75 to 81		ISO 868
Ball Indentation Hardness				
--	--	118 to 163	MPa	ISO 2039-1
H 358/30	122	--	MPa	
Thermal	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	--	139 to 226	°C	ASTM D648
0.45 MPa, Unannealed	--	111 to 221	°C	ISO 75-2/B
0.45 MPa, Unannealed, 4.00 mm, 100 mm Span ⁸	206	--	°C	ISO 75-2/Be
0.45 MPa, Annealed	--	155 to 181	°C	ISO 75-2/B
1.8 MPa, Unannealed	--	46.0 to 214	°C	ASTM D648
1.8 MPa, Unannealed	--	49.3 to 207	°C	ISO 75-2/A
1.8 MPa, Unannealed, 4.00 mm, 100 mm Span ⁸	160	--	°C	ISO 75-2/Ae
1.8 MPa, Annealed	--	57.0 to 78.0	°C	ISO 75-2/A
8.0 MPa, Unannealed	--	45.0 to 45.1	°C	ISO 75-2/C
Continuous Use Temperature				
	--	120 to 122	°C	ASTM D794
Glass Transition Temperature				
	--	54.7 to 61.5	°C	ISO 11357-2
Vicat Softening Temperature				
--	--	166 to 220	°C	ASTM D1525
--	175	--	°C	ISO 306/B120
--	170	--	°C	ISO 306/B50
--	217	--	°C	ISO 306/A50
--	--	168 to 223	°C	ISO 306
Ball Pressure Test (123 to 127°C)				
	Pass	--		IEC 60695-10-2
Melting Temperature				
--	--	222 to 226	°C	
--	--	222 to 225	°C	DSC ASTM D3418
--	--	225 to 226	°C	ISO 11357-3
--	--	210 to 226	°C	ISO 3146
CLTE				
Flow	--	2.9E-5 to 9.3E-5	cm/cm/°C	ASTM D696
Flow	--	1.9E-5 to 1.4E-4	cm/cm/°C	ASTM E831
Flow	--	1.4E-5 to 4.4E-4	cm/cm/°C	ISO 11359-2
Flow : 23 to 80°C	2.5E-5	--	cm/cm/°C	ISO 11359-2
Transverse	--	7.5E-5 to 1.2E-4	cm/cm/°C	ASTM E831
Transverse	--	1.4E-5 to 4.3E-4	cm/cm/°C	ISO 11359-2
Transverse : 23 to 80°C	1.0E-4	--	cm/cm/°C	ISO 11359-2
Transverse : 23 to 150°C	1.1E-4	--	cm/cm/°C	ISO 11359-2



Thermal	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Thermal Conductivity	--	0.25 to 0.28	W/m/K	ISO 8302
RTI Elec	125	72.5 to 140	°C	UL 746B
RTI Imp	110	74.8 to 140	°C	UL 746B
RTI Str	125	138 to 140	°C	UL 746B
Electrical	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Surface Resistivity				
--	--	1.0E+3 to 2.5E+15	ohms	ASTM D257
--	> 1.0E+15	1.0E+2 to 2.5E+15	ohms	IEC 60093
--	--	9.8E+14 to 1.0E+15	ohms	IEC 62631-3-2
Volume Resistivity				
--	--	2.5 to 2.5E+17	ohms·cm	ASTM D257
--	> 1.0E+15	13 to 2.5E+17	ohms·cm	IEC 60093
--	--	1.0E+11 to 2.5E+13	ohms·m	IEC 62631-3-1
Dielectric Strength				
--	--	2.0 to 26	kV/mm	ASTM D149
--	--	15 to 31	kV/mm	IEC 60243-1
0.800 mm, in Oil	30	--	kV/mm	IEC 60243-1
1.00 mm ⁹	24	--	kV/mm	IEC 60243-1
1.60 mm, in Oil	23	--	kV/mm	IEC 60243-1
3.20 mm, in Oil	16	--	kV/mm	IEC 60243-1
Dielectric Constant				
--	--	2.91 to 3.44		ASTM D150
--	--	3.18 to 4.02		IEC 60250
--	--	3.16		IEC 60250
50 Hz	3.30	--		IEC 60250
60 Hz	3.30	--		IEC 60250
100 Hz	3.60	--		IEC 60250
1 MHz	3.20	--		IEC 60250
--	--	3.35		IEC 62631-2-1
Dissipation Factor				
--	--	1.0E-3 to 0.078		ASTM D150
--	--	7.8E-4 to 0.020		IEC 60250
50 Hz	1.0E-3	--		IEC 60250
60 Hz	1.0E-3	--		IEC 60250
100 Hz	1.4E-3	--		IEC 60250
1 MHz	0.013	--		IEC 60250
--	--	4.0E-4 to 0.024		IEC 62631-2-1
Arc Resistance				
	--	69.5 to 180	sec	ASTM D495
Comparative Tracking Index				
--	250	587 to 600	V	IEC 60112
Solution B	150	--	V	



Flammability	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Burning Rate	--	0.0 to 100	mm/min	ISO 3795
Flame Rating				UL 94
1.5 mm	HB	--		
3.0 mm	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
--	--	743 to 960	°C	
1.0 mm	750	--	°C	
Glow Wire Ignition Temperature	--	650 to 852	°C	IEC 60695-2-13
Oxygen Index				
--	--	19 to 32	%	ASTM D2863
--	21	22 to 30	%	ISO 4589-2

Fill Analysis	VALOX™ Resin 508 - Europe	Generic PBT	Unit	Test Method
Melt Density	--	1.04 to 1.11	g/cm ³	
Melt Viscosity	--	90.9 to 219	Pa·s	ASTM D3835
Melt Specific Heat	--	2260	J/kg/°C	ASTM C351
Melt Thermal Conductivity	--	0.11	W/m/K	ASTM C177
Ejection Temperature	--	171	°C	

Injection	VALOX™ Resin 508 - Europe	Generic PBT	Unit
Drying Temperature	110 to 120	109 to 121	°C
Drying Time	2.0 to 4.0	2.8 to 6.2	hr
Drying Time, Maximum	--	10	hr
Suggested Max Moisture	0.020	0.020 to 0.043	%
Suggested Shot Size	--	60	%
Hopper Temperature	40 to 60	35 to 51	°C
Rear Temperature	230 to 245	235 to 250	°C
Middle Temperature	240 to 255	234 to 261	°C
Front Temperature	245 to 265	238 to 266	°C
Nozzle Temperature	240 to 260	239 to 261	°C
Processing (Melt) Temp	250 to 270	244 to 266	°C
Mold Temperature	40 to 100	60 to 92	°C
Injection Pressure	--	77.0 to 87.5	MPa
Holding Pressure	--	58.6 to 80.0	MPa
Back Pressure	--	0.147 to 1.64	MPa
Screw Speed	--	45 to 300	rpm
Vent Depth	--	0.019 to 0.032	mm

Injection Notes

Generic PBT

This data represents typical values that have been calculated from all products classified as: Generic PBT

This information is provided for comparative purposes only.



Extrusion	VALOX™ Resin 508 - Europe	Generic PBT	Unit
Drying Temperature	--	110 to 120	°C
Drying Time	--	3.0 to 4.0	hr
Suggested Max Moisture	--	0.040	%
Melt Temperature	--	249 to 263	°C

Extrusion Notes

Generic PBT This data represents typical values that have been calculated from all products classified as: Generic PBT
 This information is provided for comparative purposes only.

Notes

¹ A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

² Typical properties: these are not to be construed as specifications.

³ Tensile Bar

⁴ 2.0 mm/min

⁵ at Break

⁶ 80*10*4 sp=62mm

⁷ 80*10*4 mm

⁸ 120*10*4 mm

⁹ Shorttime

