THERMOLAST® K TC5PAN (Series: AD/PA)

Thermoplastic Elastomer

KRAIBURG TPE



www.ulprospector.com

Technical Data

Product Description

The AD/PA Series is your material solution for applications with excellent adhesion to PA. The compounds are available in natural and black colors

Typical applications

- · Cable clips
- · Function and design elements
- Grommets
- · Handles (hand tools and power tools etc.)
- Seals
- Thumb wheels

Material advantages

- · Adhesion to PA6 and PA6.6 up to 50 % glass fiber
- Easy coloring (compounds in natural colors)
- · Excellent adhesion
- · Excellent processing behavior
- · Insert molding possible
- · Pleasant surface feel (Soft touch)
- UL 94 HB listed
- Wide hardness range 25-80 Sh A

General			
Material Status	Commercial: Active		
Literature ¹	 Technical Datasheet (Engl 	lish)	
UL Yellow Card ²	E353857-101117932E214822-586872		
Search for UL Yellow Card	KRAIBURG TPETHERMOLAST® K		
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America
Features	Good AdhesionGood Colorability	Good ProcessabilitySoft	
Uses	Grommets	 Handles 	Seals
Appearance	 Natural Color 		
Processing Method	Injection Molding		

Physical	Nominal Value Unit	Test Method
Density	1.15 g/cm³	ISO 1183
Elastomers	Nominal Value Unit	Test Method
Tensile Stress 4 (Yield)	2.50 MPa	ISO 37
Tensile Elongation ⁴ (Break)	450 %	ISO 37
Tear Strength ⁵	13 kN/m	ISO 34-1
Compression Set ⁶		ISO 815
23°C, 72 hr	27 %	
70°C, 24 hr	78 %	
100°C, 24 hr	80 %	
Hardness	Nominal Value Unit	Test Method
Shore Hardness (Shore A)	48	ISO 7619
Flammability	Nominal Value Unit	Test Method
Flame Rating	НВ	UL 94
Additional Information	Nominal Value Unit	Test Method

Adhesion to PA6 12.0 kN/m Renault D41/1916
Form No. TDS-98862-en



Document Created: Sunday, May 22, 2016 Added to Prospector: January 2007 Last Updated: 9/25/2015

THERMOLAST® K TC5PAN (Series: AD/PA)

Thermoplastic Elastomer **KRAIBURG TPE**



www.ulprospector.com

Additional Information	Nominal Value Unit	Test Method	
Adhesion to PA66	10.0 kN/m	Renault D41/1916	
Injection	Nominal Value Unit		
Drying Temperature	60.0 to 80.0 °C		
Drying Time	2.0 to 4.0 hr		
Rear Temperature	230 to 245 °C		
Middle Temperature	250 to 260 °C		
Front Temperature	260 to 270 °C		
Mold Temperature	40.0 to 60.0 °C		
Injection Pressure	20.0 to 100 MPa		
Back Pressure	2.00 to 10.0 MPa		

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

³ Typical properties: these are not to be construed as specifications.

⁴ Type S2, 200 mm/min

⁵ Method Bb, Angle (Nicked)

⁶ Method A

THERMOLAST® K TC5PAN (Series: AD/PA)

Thermoplastic Elastomer **KRAIBURG TPE**



www.ulprospector.com

Where to Buy

Supplier

KRAIBURG TPE Duluth, GA USA

Telephone: 678-584-5020 Web: http://www.kraiburgtpe.com/

Distributor

Chase Plastic Services, Inc.

Chase Plastics Services is a North American distributor with representatives throughout the region. Please find your rep here:

http://www.chaseplastics.com/contact/locations

Telephone: 800-232-4273

Web: http://www.chaseplastics.com/ Availability: North America

Resin Resource, Inc. Telephone: 877-652-3431

Web: http://www.resinresourceinc.com/

Availability: North America



Form No. TDS-98862-en