

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.5 / *	%	ISO 294-4, 2577
^{[C]: CAMPUS}			

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	210 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
^{[C]: CAMPUS}			

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Surface resistivity	* / 1E14	Ohm	IEC 60093
^[C] Electric strength	34 / -	kV/mm	IEC 60243-1
^[C] Comparative tracking index	600 / -	-	IEC 60112
^{[C]: CAMPUS}			

Other properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Density	1250 / -	kg/m³	ISO 1183
^{[C]: CAMPUS}			

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa