

ECOZEN[®]

T110

**ECOZEN**

Product description

ECOZEN, conceived and developed by SK Chemicals is a bio-based, heat-resistant, and transparent bio-copolyester. Available in 5 distinct product lines, each containing all the advantages of conventional PETG resins, like high transparency, easy-processing, and chemical resistance. ECOZEN also has increased heat resistance, while using eco-friendly materials.

Applications

- Cosmetic
- Home appliance
- Sheet & others

Key Attributes

- High flowability
- High HDT

Notes

The data listed here is preliminary data sheet of product. Therefore this sheet should not be used to establish specification limits or used alone as a basis for design. This information is not intended as a warranty of any kind. Customers must make their own representative test and assume all risks of use, whether used alone or in combination with other products. SK Chemicals assumes no obligation or liability of any advice furnished by it or results obtained with respect to these products. All warranties of merchantability for a particular purpose or use are excluded and disclaimed.

Typical properties for

ECOZEN[®] T110

ASTM Method

Product Information

Property	Test Method	Unit	Result
Specific Gravity	ASTM D792	-	1.27
Mold Shrinkage	ASTM D955	%	0.2 ~ 0.5
Rockwell Hardness	ASTM D785	R-scale	119
Tensile Strength @ Yield	ASTM D638	Kgf/cm ²	520
Tensile Strength @ Break	ASTM D638	Kgf/cm ²	540
Elongation @ Yield	ASTM D638	%	6.8
Elongation @ Break	ASTM D638	%	200
Flexural Strength	ASTM D790	Kgf/cm ²	820
Flexural Modulus	ASTM D790	Kgf/cm ²	19,500
Izod Impact Strength Notched @ 23	ASTM D256	J/m	860
Heat Distortion Temperature @ 0.455 MPa / @ 1.820 MPa	ASTM D648		99 / 85
Haze	ASTM D1003	%	< 1.0
Transmittance	ASTM D1003	%	86

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si,
Gyeonggi-do, Republic of Korea [13494]
TEL : +82-2-2-2008-2008
FAX : +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan,
Republic of Korea [44784]
TEL : +82-52-256-0121
FAX : +82-52-256-0652

Typical properties for

ECOZEN[®] T110

ISO Method

Product Information

Property	Test Method	Unit	Result
Specific Gravity	ASTM D792	-	1.27
Mold Shrinkage	ASTM D955	%	0.2 ~ 0.5
Rockwell Hardness	ASTM D785	R - scale	119
Tensile Strength @ Yield	ISO 527	MPa	49
Tensile Strength @ Break	ISO 527	MPa	48
Elongation @ Yield	ISO 527	%	5.7
Elongation @ Break	ISO 527	%	150
Flexural Strength	ISO 178	MPa	73
Flexural Modulus	ISO 178	MPa	1,800
Izod Impact Strength Notched @ 23	ISO 180	KJ/m2	93
Heat Distortion Temperature @ 0.455 MPa / @ 1.820 MPa	ISO 75		97 / 81
Haze	ASTM D1003	%	< 1.0
Transmittance	ASTM D1003	%	86

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si,
Gyeonggi-do, Republic of Korea [13494]
TEL : +82-2-2-2008-2008
FAX : +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan,
Republic of Korea [44784]
TEL : +82-52-256-0121
FAX : +82-52-256-0652