

ALTECH PA6 A 2030/109 GF30

(Last update: 06.10.2016)

Base Polymer	Polyamide 6
Filler/Additive System	30 % glass fibres
Special Features	heat ageing stabilisation,easy release (demoulding),high flow
Typical Applications	housings,various

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-12 h dependant on moisture content max. moisture content <0,15 %
Processing Conditions	injection moulding melt temperature 270-290 °C injection moulding mould temperature 80-100 °C
Storage	dry, protected from light not above 30°C

Properties	dry/cond.	Dimension	Test Norm
Mechanical Properties			
Flexural modulus	8000 / 4700	MPa	ISO 178
Flexural strength	240 / 110	MPa	ISO 178
Tensile modulus	9000 / 5100	MPa	ISO 527-1/-2
Tensile strength	170 / -	MPa	ISO 527-1/-2
Tensile strength at break	- / 90	MPa	ISO 527-1/-2
Tensile elongation at break	3 / 6	%	ISO 527-1/-2
Charpy notched impact 1eA	10 / 19	kJ/m ²	ISO 179/1eA
Charpy notched impact 1eA -40°C	7	kJ/m ²	ISO 179/1eA
Charpy impact strength 1eU	70 / 89	kJ/m ²	ISO 179/1eU
Charpy impact strength 1eU -40°C	53	kJ/m ²	ISO 179/1eU
Thermal Properties			
Vicat B50	215 / *	°C	ISO 306
HDT / A (1,8 MPa)	200 / *	°C	ISO 75-1/-2
DSC (Melt Point)	221 / *	°C	ISO 11357
Rheological Properties			
Relative Viscosity (m-Cresol,c = 10 g/l)	3	-	ISO 307
Physical Properties			
Density	1360 / -	kg/m ³	ISO 1183
Flammability			
Flammability, 0.75 mm	HB / *	class	UL 94
Yellow Card available	yes / *	-	-

ALTECH PA6 A 2030/109 GF30

(Last update: 06.10.2016)

These are guide values and not a specification. The test values mentioned are representative values only and not binding minimum or maximum figures. These test values have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions.

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended. The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.