

Schulaketon GF 30 4DE ORANGE

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fiber reinforced aliphatic Polyketon, flame-retardant, halogen free. Available in orange colour.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Flame Retardant	• Halogen Free	
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PK GF30 FR(40)		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.45 g/cm ³	1.45 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (240°C/5.0 kg)	17 cm ³ /10min	17 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.16E+6 psi	8000 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	18900 psi	130 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.5 %	3.5 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	6.2 ft·lb/in ²	13 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	26 ft·lb/in ²	55 kJ/m ²	ISO 179/1eU

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	408 °F	209 °C	ISO 75-2/af
RTI Elec			UL 746B
0.016 in (0.40 mm)	122 °F	50.0 °C	
0.024 in (0.60 mm)	122 °F	50.0 °C	
0.031 in (0.8 mm)	122 °F	50.0 °C	
0.06 in (1.6 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	
RTI Imp			UL 746B
0.016 in (0.40 mm)	122 °F	50.0 °C	
0.024 in (0.60 mm)	122 °F	50.0 °C	
0.031 in (0.8 mm)	122 °F	50.0 °C	
0.06 in (1.6 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	
RTI Str			UL 746B
0.016 in (0.40 mm)	122 °F	50.0 °C	
0.024 in (0.60 mm)	122 °F	50.0 °C	
0.031 in (0.8 mm)	122 °F	50.0 °C	
0.06 in (1.6 mm)	122 °F	50.0 °C	
0.12 in (3.0 mm)	122 °F	50.0 °C	

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Electric Strength 73°F (23°C), 0.0394 in (1.00 mm), in Air	970 V/mil	38 kV/mm	IEC 60243-1


Schulaketon GF 30 4DE ORANGE

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Comparative Tracking Index	600 V	600 V	IEC 60112
High Amp Arc Ignition (HAI)			UL 746A
0.016 in (0.40 mm)	PLC 0	PLC 0	
0.024 in (0.60 mm)	PLC 0	PLC 0	
0.03 in (0.8 mm)	PLC 0	PLC 0	
0.06 in (1.6 mm)	PLC 0	PLC 0	
0.12 in (3.0 mm)	PLC 0	PLC 0	
Hot-wire Ignition (HWI)			UL 746A
0.016 in (0.40 mm)	PLC 0	PLC 0	
0.024 in (0.60 mm)	PLC 0	PLC 0	
0.03 in (0.8 mm)	PLC 0	PLC 0	
0.06 in (1.6 mm)	PLC 0	PLC 0	
0.12 in (3.0 mm)	PLC 0	PLC 0	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm), Self-Extinguishing	0.0 in/min	0.0 mm/min	ISO 3795
0.0787 in (2.00 mm), Self-Extinguishing	0.0 in/min	0.0 mm/min	FMVSS 302
Flame Rating			
0.016 in (0.40 mm)	V-0	V-0	UL 94 IEC 60695-11-10, -20
0.024 in (0.60 mm)	V-0	V-0	UL 94 IEC 60695-11-10, -20
0.031 in (0.8 mm)	V-0	V-0	UL 94
0.06 in (1.6 mm)	• V-0 • 5VA	• V-0 • 5VA	UL 94 IEC 60695-11-10, -20
0.12 in (3.0 mm)	• V-0 • 5VA	• V-0 • 5VA	UL 94 IEC 60695-11-10, -20
0.03 in (0.8 mm)	V-0	V-0	IEC 60695-11-10, -20
Glow Wire Flammability Index			IEC 60695-2-12
0.024 in (0.60 mm)	1760 °F	960 °C	
0.031 in (0.8 mm)	1760 °F	960 °C	
0.06 in (1.6 mm)	1760 °F	960 °C	
0.12 in (3.0 mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.024 in (0.60 mm)	1520 °F	825 °C	
0.031 in (0.8 mm)	1520 °F	825 °C	
0.06 in (1.6 mm)	1560 °F	850 °C	
0.12 in (3.0 mm)	1520 °F	825 °C	

Schulaketon GF 30 4DE ORANGE

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Suggested Max Moisture	0.15 %	0.15 %
Processing (Melt) Temp	428 to 446 °F	220 to 230 °C
Mold Temperature	140 to 212 °F	60 to 100 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	290 to 1160 psi	2.00 to 8.00 MPa
Screw Speed	< 591 in/min	< 15 m/min

Injection Notes

Before start, nozzle, screw, barrel and hot-runner have to be cleaned with Polyolefin. Contamination of other material leads to degradation or crosslinking of SCHULAKETON®.

Avoid shut down for more than 8 minutes at moulding temperature, because of degradation and crosslinking of SCHULAKETON®. Purge with Polyolefin!

Mould surfaces in contact with melt are recommended to be of non-corrosive steel, chrome content >12%

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2022

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Schulaketon GF 30 4DE ORANGE

Polyketone, Aliphatic
LyondellBasell Industries
Engineering Plastics

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.