HOSTAFORM® FK 1:25 - POM

Description

acetal color masterbatch/concentrate

Hostaform® FK color masterbatches (color concentrates) are for use with other acetal products based in Celanese's acetal copolymer. Hostaform® FK color masterbatches are specially designed to provided color to other Celcon® and Hostaform® grades with minimal affect on performance properties. It is not meant to be molded as a stand alone product. FDA compliant Hostaform® FK color masterbatches are available in specific colors. Please contact Celanese for details.

Thermal properties		Value	Unit	Test Standard
Melting temperature, 10°C/min		165	°C	ISO 11357-1/-3
Typical injection moulding pr	ocessing conditions			
Pre Drying		Value	Unit	
Drying time		3 - 4	h	
Drying temperature		100 - 120	°C	
Characteristics				
Special Characteristics	Auto spec approved			
Product Categories	Color concentrate			
Delivery Form	Pellets			

Other Approvals

OEM	Specification
Bosch	N28 BN90-21-004 (GRAY)
Bosch	N28 BN90-21-008 (BROWN)
Bosch	N28 BN90-21-005 (BROWN)
Bosch	N28 BN90-21-005 (BROWN)

Contact

Americas	Asia	Europe	
8040 Dixie Highway	4560 Jinke Road	Am Unisys-Park 1	
Florence, KY 41042 USA	Zhang Jiang Hi Tech Park	65843 Sulzbach, Germany	
Product Information Service	Shanghai 201210 PRC	Product Information Service	
t: +1-800-833-4882	Customer Service	t: +49-800-86427-531	
t: +1-859-372-3244	t: +86 21 3861 9288	t: +49-(0)-69-45009-1011	
Customer Service	e: info-engineeredmaterials-asia@celanese.come: info-engineeredmaterials-eu@celanese.com		
t: +1-800-526-4960			
t: +1-859-372-3214			
e: info-engineeredmaterials-am@celanese.co	m		

General Disclaimer

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colorants or other additives may cause significant variations in data values. Properties of molded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The

HOSTAFORM® FK 1:25 - POM

information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products. The products mentioned herein are not intended for use in medical or dental implants.

Trademark

© 2021 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.