



DATA SHEET

PC TAROLON 2500

Polycarbonate medium viscosity, standard grade for general purpose.

Available: all colors, UV stabilized (L), release agent (W).

	DRYING - conditions	Melt temperature:	260 - 290°C
Pre-heater:	120 - 130°C / 3 h	Mould temperature:	80 - 100°C
Dryer:	100 - 110°C / 1-2 h	Rate of injection:	MEDIUM - HIGH

PROPERTY	METHOD	DIN	ISO	ASTM	unit	VALUE	condition
ELECTRICAL							
Volume Resistivity		5348		D257	Ohm cm	>10exp(15)	
Tracking Resistance (CTI - Method A)	IEC 112				Volt	225	
Electric Strength				D149	kV/mm	20	2 mm
PHYSICAL							
Melt Flow Index		5373	R292	D123	g/10'	18	300°C - 1,2 Kg
Density (23 °C)		5347	R118	D792	Mg/m^3	1,20	
Water Absorption (24h / 23°C)		5349	R62	D570	%	0,12	
Water Absorption at Saturation		5349	R62	D570	%	0,35	
Mould Shrinkage (Parallel)				D955	%	0,5 - 0,7	
Mould Shrinkage (Normal)				D955	%	0,5 - 0,7	
MECHANICAL							
IZOD Notched Impact		-	180	D256	J/m	600	+23°C - 3,2 mm
IZOD Unnotched Impact		-	-	D256	J/m	N.B.	
CHARPY Notched Impact		5345	R179	D256	kJ/m^2	25	+23°C - 6x4x50 mm
CHARPY Unnotched Impact		5345	R179	D256	kJ/m^2	>300	+23°C - 6x4x50 mm
Tensile Modulus		5345	R527	D638	N/mm^2	2300	
Flexural Modulus		5345	R178	D790	N/mm^2	2500	
Elongation at Break		5345	R527	D638	%	85	
Tensile Yield Strength		5345	R527	D638	N/mm^2	62	
Flexural Yield Strength		5345	R178	D790	N/mm^2	85	
FLAMMABILITY							
Oxygen index				D286	%	26	
Flame Behaviour (1,6 mm)	UL 94					V2	
Glow Wire Test (2 mm)	IEC 695-2-1				°C	850	
THERMAL							
VICAT Temperature (1 kg)		5346	R306	D152	°C	150	50°C / h
Heat Deflection Temperature (1,82 N/mm^2)		5346	R75	D648	°C	140	120°C / h
Ball Pressure Test	VDE 0470				°C	125	
Continuous service temperature (20.000 h)	IEC 216				°C	120	
Coefficient of linear thermal expansion		5375		D696	K^-1	7x10exp(-5)	-30°C /+30°C

These value are for natural color only. Colorant or other additives may alter some or all of these property. The data listed here fall within the normal range of product properties, but they should not be used to establish specification limits nor used alone as the basis of design.