



TEREZ ABS 5020			
ABS			Ter Plastics
Product Texts			
Fast flowing standard ABS. For complex multi-cavity molds with a long flow distance.			
Rheological properties			
	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	36	g/10min	ISO 1133
MFI temperature	220	°C	-
MFI load	10	kg	-
Mechanical properties			
	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2300	MPa	ISO 527-1/-2
Yield stress	45	MPa	ISO 527-1/-2
Yield strain	2.5	%	ISO 527-1/-2
Strain at break	20	%	ISO 527-1/-2
Charpy notched impact strength, +23°C	19	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	9	kJ/m ²	ISO 179/1eA
Flexural modulus, 23°C	2400	MPa	ISO 178
Thermal properties			
	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	95	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Other properties			
	Value	Unit	Test Standard
ISO Data			
Density	1040	kg/m ³	ISO 1183