

SABIC Geloy XTPMFR15 ASA+PC (Europe-Africa-Middle East) (Unverified Data)**

Categories: [Polymer](#); [Thermoplastic](#); [ASA Polymer](#); [Polycarbonate \(PC\)](#); [Polycarbonate/ASA Alloy](#); [Unreinforced](#)

Material Notes: Geloy XTPMFR15 is a chlorine and bromine free flame retardant ASA/PC blend with improved impact performance/ductility and an UL94 rating of V0 at 1.5mm. This grade has a fl rating according UL746C.

This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Vendors: No vendors are listed for this material. Please [click here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183
Viscosity	138000 cP @Temperature 260 °C	138000 cP @Temperature 500 °F	melt; 1500 sec-1; ISO 11443
Melt Flow <input type="checkbox"/>	18 g/10 min @Load 2.16 kg, Temperature 260 °C	18 g/10 min @Load 4.76 lb, Temperature 500 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	27 g/10 min @Load 10.0 kg, Temperature 220 °C	27 g/10 min @Load 22.0 lb, Temperature 428 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	30 g/10 min @Load 10.0 kg, Temperature 220 °C	30 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa 47.0 MPa 48.0 MPa	6530 psi 6820 psi 6960 psi	50 mm/min; ISO 527 Type I, 50 mm/min; ASTM D 638 Type I, 5 mm/min; ASTM D 638
Tensile Strength, Yield	56.0 MPa 57.0 MPa 61.0 MPa	8120 psi 8270 psi 8850 psi	50 mm/min; ISO 527 Type I, 5 mm/min; ASTM D 638 Type I, 50 mm/min; ASTM D 638
Elongation at Break	55 % 60 % 62 %	55 % 60 % 62 %	Type I, 50 mm/min; ASTM D 638 50 mm/min; ISO 527 Type I, 5 mm/min; ASTM D 638
Elongation at Yield	4.0 % 4.0 % 4.0 %	4.0 % 4.0 % 4.0 %	Type I, 50 mm/min; ASTM D 638 Type I, 5 mm/min; ASTM D 638 50 mm/min; ISO 527
Tensile Modulus	2.25 GPa 2.50 GPa	326 ksi 363 ksi	1 mm/min; ISO 527 50 mm/min; ASTM D 638
Flexural Yield Strength	88.0 MPa	12800 psi	2 mm/min; ISO 178
Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
Izod Impact, Notched <input type="checkbox"/>	1.18 J/cm @Temperature -30.0 °C	2.21 ft-lb/in @Temperature -22.0 °F	ASTM D 256
	7.00 J/cm @Temperature 23.0 °C	13.1 ft-lb/in @Temperature 73.4 °F	ASTM D 256
Izod Impact, Notched (ISO) <input type="checkbox"/>	15.0 kJ/m ² @Temperature -30.0 °C	7.14 ft-lb/in ² @Temperature -22.0 °F	80*10*4; ISO 180/1A
	26.0 kJ/m ² @Temperature 0.000 °C	12.4 ft-lb/in ² @Temperature 32.0 °F	80*10*4; ISO 180/1A
	50.0 kJ/m ² @Temperature 23.0 °C	23.8 ft-lb/in ² @Temperature 73.4 °F	80*10*4; ISO 180/1A
Charpy Impact, Notched	5.80 J/cm ² @Temperature 23.0 °C	27.6 ft-lb/in ² @Temperature 73.4 °F	V-notch Edgew 80*10*4 sp=62mm; ISO 179/1eA

Electrical Properties	Metric	English	Comments
Hot Wire Ignition, HWI	>= 120 sec	>= 120 sec	PLC code 0; UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	surface, PLC code 0; UL 746A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.0 μm/m-°C @Temperature -40.0 - 40.0 °C	37.8 μin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
CTE, linear, Transverse to Flow	70.0 μm/m-°C	38.9 μin/in-°F	ISO 11359-2

	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	99.0 °C	210 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	88.0 °C	190 °F	Flatw 80*10*4 sp=64mm; ISO 75/ Af
Vicat Softening Point	103 °C	217 °F	Rate B/50; ISO 306
	104 °C	219 °F	Rate B/120; ISO 306
	111 °C	232 °F	Rate A/50; ISO 306
Flammability, UL94 <input type="checkbox"/>	V-1	V-1	UL 94
	@Thickness 1.20 mm	@Thickness 0.0472 in	
	V-0	V-0	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	5VB	5VB	UL 94
Oxygen Index	@Thickness 2.00 mm	@Thickness 0.0787 in	
	5VA	5VA	UL 94
	@Thickness 3.00 mm	@Thickness 0.118 in	
	30 %	30 %	LOI; ISO 4589
	800 °C	1470 °F	IEC 60695-2-13
Glow Wire Ignition Temperature <input type="checkbox"/>	@Thickness 2.00 mm	@Thickness 0.0787 in	
	800 °C	1470 °F	IEC 60695-2-13
	@Thickness 3.00 mm	@Thickness 0.118 in	
	825 °C	1520 °F	IEC 60695-2-13
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Glow Wire Flammability Index	850 °C	1560 °F	IEC 60695-2-13
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	960 °C	1760 °F	IEC 60695-2-12
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Descriptive Properties

UV-light, water exposure/immersion	F1	UL 746C
------------------------------------	----	---------

**

This data sheet is not an active part of MatWeb and the information on it should not be considered reliable.

Inactive data sheets have usually been replaced with newer information on the same material. If this is the case, you can find the active data sheet by using any of our search tools, including the Quick Search box in the upper part of this page.

If you are unable to locate an active data sheet for this material, then this material is likely discontinued, although various other reasons may be behind its removal. In any event, do not rely on the information on this page to be accurate or maintained.

You may have reached this data sheet through an outdated bookmark or link. Please update your bookmark accordingly. We apologize if you have accessed this page through MatWeb's usual search tools.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's [terms of use](#) regarding this information. [Click here](#) to view all the property values for this datasheet as they were originally entered into MatWeb.